



(43) International Publication Date
24 February 2005 (24.02.2005)

PCT

(10) International Publication Number
WO 2005/016882 A1

(51) International Patent Classification: C07D 209/86,
C08F 26/12

(21) International Application Number:
PCT/CA2004/001509

(22) International Filing Date: 16 August 2004 (16.08.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/495,113 15 August 2003 (15.08.2003) US

(71) Applicant (for all designated States except US): UNIVER-
SITE LAVAL [CA/CA]; Pavillon des Sciences de l'Éduca-
tion, local 1374, Quebec, Quebec G1K 7P4 (CA).

(72) Inventors; and

(75) Inventors/Applicants (for US only): LECLERC, Mario
[CA/CA]; 145 Gérard-Morisset, App. 103, Quebec, Que-
bec G1S 4V5 (CA). MORIN, Jean-François [CA/CA];
861 Rue Baugis, Beauport, Quebec G1C 5Z1 (CA).

(74) Agents: DUBUC, J. et al.; Goudreau Gare Dubuc, Stock
Exchange Tower, 800 Place Victoria, Suite 3400, P.O. Box
242, Montreal, Quebec H4Z 1B9 (CA).


(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).


Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.



(54) Title: MONOMERS, OLIGOMERS AND POLYMERS OF 2-FUNCTIONALIZED AND 2,7-DIFUNCTIONALIZED CAR-
BAZOLES



(I)

(57) Abstract: The present invention relates to 2-functionalized and 2,7-di-
functionalized carbazoles and 2,7-carbazolenenevinylene oligomers and poly-
mers. More specifically, the present invention relates to a compound of
Formula (I): wherein R¹ is selected from the group consisting of H, alkyl,
and aryl; and wherein R² and R³ are independently selected from the group
consisting of H, alkyl, formyl, hydroxymethyl, trihydroxymethyl, acetonitrile,
chloromethyl, methylphosphonate, methyltriphenylphosphonium and vinyl.

The oligomers and polymers are used in field-effect transistors, light-emitting devices such as light-emitting diodes, and solar cells.

TITLE OF THE INVENTION

[0001] MONOMERS, OLIGOMERS AND POLYMERS OF 2-FUNCTIONALIZED AND 2,7-DIFUNCTIONALIZED CARBAZOLES.

FIELD OF THE INVENTION

5 [0002] The present invention relates to a new class of organic material. More specifically, the present invention is relates to monomers, oligomers and polymers of 2 functionalized and 2,7-difunctionalized carbazoles.

BACKGROUND OF THE INVENTION

10 [0003] Conjugated polymeric and oligomeric organic materials are subject to important investigations from both academic and industrial laboratories, due to their great potential for applications in light-emitting diodes, field-effect transistors, sensors, solar cells, etc.¹⁻⁷

15 [0004] The relatively low cost synthesis, ease of processability and the great tunability of their optical and electrical properties through chemical modification are just some of the advantages provided by organic semi-conducting materials over their inorganic counter parts.

20 [0005] Important developments in modern synthetic chemistry, especially the chemistry of carbon-carbon bond formation (Kumada, Stille, Yamamoto, Suzuki, Heck, and Sonogashira couplings, etc.) have allowed the synthesis of well-defined conjugated oligomers and polymers having a high degree of purity and improved physical properties in comparison to those obtained by traditional oxidative couplings. Moreover, a good understanding of the structure-property relationship, combined with the many new, highly selective synthetic methods now available, have allowed for the development of a nearly unlimited number of

structures having specific properties and performances approaching those of their inorganic counterparts. Small molecules having planar structures generally lead to highly ordered solid π - π^* interactions. Therefore, 2,7-carbazolenevinylene-based materials can thus be used in electronic devices requiring good charge transport properties, such as in field-effect transistors. Depending on the sought-after applications, different building blocks, such as thiophene, pyrrole, phenylene, fluorene and carbazole can be used, irrespective of their specific properties. In this regard, 2,7-carbazole-based well-defined polymers have been recently prepared.^{8,9} Their good fluorescence properties have led to the preparation and testing in light-emitting diodes of electroluminescent polymers spanning the entire visible range.^{10,11,12} The introduction of a vinylene unit into the polymer backbone is known to decrease the band gap due to the relatively low dihedral angle between the vinylene unit and a common aryl group. Consequently, medium to low band gap materials can be obtained, allowing for the preparation of a wide variety of luminescent polymers providing for green to red-light emissions.

[0006] However, the development of new building blocks for the preparation of 2,7-carbazolenevinylene-based materials remains a challenge to any chemist or physicist desirous of optimizing material performance in electronic devices requiring good charge transport properties.


[0007] The present invention seeks to meet these needs and other needs.

[0008] The present description refers to a number of documents, the content of which is herein incorporated by reference in their entirety.

SUMMARY OF THE INVENTION

[0009] The present invention relates to 2 functionalized and 2,7-difunctionalized carbazoles as well as to methods for preparing these carbazoles.


More specifically, the present invention relates to a compound of Formula I:




Formula I

[0010] wherein R^1 is selected from the group consisting of H, alkyl, and aryl;
 5 and wherein R^2 and R^3 are independently selected from the group consisting of H, alkyl, formyl, hydroxymethyl, trityloxymethyl, acetonitrile, chloromethyl, methylphosphonate, methyltriphenylphosphonium and vinyl.

[0011] Yet more specifically, the present invention relates to 2
 10 functionalized and 2,7-difunctionalized carbazoles selected from the group consisting of:






[0012] The present invention also relates to 2,7-carbazolenevinylene-based oligomers as well as to methods for preparing these oligomers.

5 **[0013]** Yet more specifically, the present invention relates to a 2,7-carbazolenevinylene-based oligomer comprising the reaction product of a first compound of Formula I and at least a second compound, the second compound being either a compound of Formula I; benzaldehyde; 5,5'-diformyl-2,2'-bithiophene, 4-bromo-1,1'-biphenyl; benzyl cyanide; or 1,4-bis(methylphosphonate)benzene.

10 **[0014]** In a first particular embodiment, the present invention relates to a


2,7-carbazolenevinylene-based oligomer having the formula:



[0015] wherein R^1 is selected from the group consisting of H, alkyl, and aryl.

[0016] In a second particular embodiment, the present invention relates to a


5 2,7-carbazolenevinylene-based oligomer having the formula:



[0017] wherein R^1 is selected from the group consisting of H, alkyl, and aryl.

[0018] In a third particular embodiment, the present invention relates to a


10 2,7-carbazolenevinylene-based oligomer having the formula:



[0019] wherein R^1 is selected from the group consisting of H, alkyl, and aryl.


[0020] In a fourth particular embodiment, the present invention relates to a

2,7-carbazolenevinylene-based oligomer having the formula:




[0021] wherein R^1 is selected from the group consisting of H, alkyl, and aryl.

[0022] In a fifth particular embodiment, the present invention relates to a
5 2,7-carbazolenevinylene-based oligomer having the formula:



[0023] wherein R^1 is selected from the group consisting of H, alkyl, and aryl.

[0024] In a sixth particular embodiment, the present invention relates to a
10 2,7-carbazolenevinylene-based oligomer having the formula:




[0025] wherein R^1 is selected from the group consisting of H, alkyl, and aryl.

[0026] The present invention additionally relates to 2,7-carbazolenevinylene-based polymers as well as to methods of preparing these
15 polymers.


[0027] Yet more specifically, the present invention relates to 2,7-carbazolenevinylene-based polymers comprising the reaction product of a compound of Formula I and optionally at least one compound selected from the group consisting of 2,5-dioctyloxy-1,4-diformylbenzene; 2,5-bis(diphenylamino)terephthaldicarboxaldehyde; {4-(2-ethylhexyloxy)-phenyl}-bis-(4'-formylphenyl); 6,6'-dibromo-2,2'-bis(2"-ethylhexyloxy)-1,1'-binaphthyl; and 3-hexyl-2,5-bis(methylphosphonate)thiophene.

[0028] In a first particular embodiment, the present invention relates to a 2,7-carbazolenevinylene-based polymer having the formula:



[0029] wherein "n" is an integer ranging from 5 to 100.


[0030] In a second particular embodiment, the present invention relates to a 2,7-carbazolenevinylene-based polymer having the formula:




[0031] wherein "n" is an integer ranging from 5 to 100.

[0032] In a third particular embodiment, the present invention relates to a 2,7-carbazolenevinylene-based polymer having the formula:

[0034] In a fourth particular embodiment, the present invention relates to a 2,7-carbazolenevinylene-based polymer having the formula:




[0036] In a fifth particular embodiment, the present invention relates to a 2,7-carbazolenevinylene-based polymer having the formula:



[0037] wherein "n", "m" and "o" are integers ranging from 5 to 100.


[0038] In a sixth particular embodiment, the present invention relates to a 2,7-carbazolenevinylene-based polymer having the formula:



5

[0039] wherein "n" is an integer ranging from 5 to 100.

[0040] In a seventh particular embodiment, the present invention relates to a 2,7-carbazolenevinylene-based polymer having the formula:



[0041] wherein "n" is an integer ranging from 5 to 100.

[0042] The present invention also relates to 2,7-carbazolenevinylene-based oligomers and polymers for use in applications including but not limited to field-effect transistors, light-emitting devices such as light-emitting diodes, and solar cells.

[0043] Other objects, advantages and features of the present invention will become more apparent upon reading of the following non-restrictive description of preferred embodiments thereof, given by way of example only with reference to the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0044] In the appended drawings:

[0045] Figure 1 illustrates the synthesis of novel 2,7-difunctionalized carbazoles;

[0046] Figure 2 illustrates the synthesis of 2-functionalized carbazoles;

[0047] Figure 3 illustrates the chemical structure of various oligomers;

[0048] Figure 4 illustrates the chemical structure of various polymers;

[0049] Figure 5 provides a schematic illustration of the polymerization yield obtained for various polymers as well as their molecular weight;

[0050] Figure 6 provides a schematic illustration of the optical properties of

various polymers;

[0051] Figure 7 provides a schematic illustration of the optical and electrochemical properties of various oligomers; and

[0052] Figure 8 illustrates the absorption and emission spectra of PCCVP in
5 chloroform as well as in the solid state.

DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

[0053] As used herein, the term "alkyl" is intended to include linear, branched and cyclic structures, as well as combinations thereof, having up to 10 carbon atoms. Non-limiting examples of alkyl groups include methyl, ethyl,
10 propyl, isopropyl, cyclopropyl, butyl, sec-butyl, tert-butyl, cyclobutyl, pentyl, cyclopentyl, hexyl, cyclohexyl, heptyl, cycloheptyl, octyl, cyclooctyl, 2-ethylhexyl, nonyl and decyl.

[0054] As used herein, the term "alkoxy" is intended to include such alkyl groups as defined above attached to an oxygen atom. Non-limiting
15 examples of alkyl groups include methoxy, ethoxy, propoxy, isopropoxy, cyclopropoxy, butoxy, sec-butoxy, tert-butoxy, cyclobutoxy, pentoxy, cyclopentoxy, hexyloxy, cyclohexyloxy, heptyloxy, cycloheptyloxy, octyloxy, cyclooctyloxy, nonyloxy and decyloxy.

[0055] As used herein, the term "aryl" is intended to mean an
20 aromatic ring structure having, for example, 6-10 carbon atoms, preferably a phenyl group or a phenyl group substituted with an alkyl or alkoxy group, wherein the terms alkyl and alkoxy are as defined above.

[0056] As used herein, the term "oligomer" is intended to mean a molecule composed of a at least 2 linked monomer units; more preferably, 2 to 4 linked monomer units.

[0057] As used herein, the term "polymer" is intended to mean a molecule composed of a at least 5 linked monomer units; preferably, 5 to 500 linked monomer units, and more preferably 5 to 100 linked monomer units. It is to be understood that the polymers as described herein may be composed of different monomeric units.

Experimental

[0058] **Characterization:** Number-average (M_n) and weight-average (M_w) molecular weights were determined by size exclusion chromatography (SEC) using an HPLC pump and a Waters UV-vis detector. A calibration curve was prepared using a series of monodispersed polystyrene standards in THF (HPLC grade, Aldrich). UV-vis absorption spectra were recorded on a Hewlett-Packard diode-array spectrophotometer (model 8452A) using quartz cells (1-cm path length). Optical band gaps were calculated from the onset of the UV-visible absorption band. For solid-state measurements, polymer solutions in chloroform were cast on quartz plates. Fluorescence spectra were measured using a Varian Eclipse spectrofluorimeter. For fluorescence analyses in solution, the polymer concentration was about 10^{-6} M. The fluorescence quantum yield (ϕ_F) for PCVBN was determined in argon-saturated chloroform solutions at 298 °K using 9,10-diphenylanthracene (Aldrich) in cyclohexane as the standard ($\phi_F = 0.90$). The fluorescence quantum yield for PCV, PCVP and PCVDPATA was determined against PQC10 ($\phi_F = 0.11$) in chloroform¹³, while 1,3,5,7,8-pentamethyl-2,6-diethylpyrromethane•BF₂ ($\phi_F = 0.83$) in ethanol¹⁴ was used for PCCVP and PCVDPAP. For solid-state fluorescence analyses, polymer solutions were cast on

a triangular quartz cell and placed at 45° with respect to the incident beam. All fluorescence excitation spectra were found to be equivalent to their respective absorption spectra.

[0059] Materials: Chloroform (spectrograde) was purchased from Aldrich and used as received. 2,5-bis(diphenylamino)terephthalaldehyde, [4-(2-ethylhexyloxy)-phenyl]-bis-(4'-formylphenyl)amine, 2,5-dioctyloxy-1,4-diformylbenzene, 6,6'-dibromo-2,2'-bis(2"-ethylhexyloxy)-1,1'-binaphthyl and 3-hexyl-2,5-bis(methylphosphonate)thiophene were synthesized as previously described in literature.^{15,16,17,18,19}

[0060] The present invention is illustrated in further detail by the following non-limiting examples.

[0061] The following is a detailed description of precursors and reagents as well as the reaction schemes used to prepare the oligomers and polymers of the present invention. The number in between parenthesis refers to compounds in the reaction schemes depicted in Figures 1-3.

[0062] 4-bromo-3-nitrobenzoic acid (1): In a 1 L flask, 4-bromobenzoic acid (50.0 g, 0.25 mol, Aldrich Co.), nitric acid (450 mL) and fuming nitric acid (100 mL) were mixed and refluxed for 24 h. The mixture was cooled at 0°C and the white precipitate filtered through a Büchner funnel, washed thoroughly with water and dried under reduced pressure to provide 53.9 g of the title product as a white solid. M.P.: 202-204°C (Yield: 88%). ¹H NMR (300 MHz, Acetone-d₆, ppm): 11.37 (s, 1H); 8.47 (d, 1H, J = 1.9 Hz); 8.16 (dd, 1H, J = 6.6 and 1.6 Hz); 8.04 (d, 1H, J = 8.3 Hz). ¹³C NMR (75 MHz, Acetone-d₆, ppm): 206.35; 165.07; 136.29; 134.55; 132.26; 126.90; 119.08.

[0063] 4-bromo-3-nitrobenzyl alcohol (2): To a solution of compound 1

(45.0 g, 0.18 mol) in 700 mL of anhydrous THF was slowly added borane-dimethylsulfide complex (19.4 mL, 0.19 mol, 10.0M in dimethylsulfide, Aldrich Co.) at room temperature. The mixture was stirred for 48 h under argon at room temperature and then quenched with 250 mL of distilled water. Diethyl ether (500 mL) was added and the organic layer was washed three times with water (250 mL) followed by brine (250 mL). The combined organic fractions were dried over magnesium sulfate and the solvent was removed under reduced pressure to provide 41.3 g of the title product as a yellow solid. M.P.: 61-62°C (Yield: 98%). ¹H NMR (400 MHz, CDCl₃, ppm): 7.81 (s, 1H); 7.67 (d, 1H, *J* = 8.3 Hz); 7.38 (d, 1H, *J* = 8.5 Hz); 4.71 (s, 2H); 2.61 (s, 1H). ¹³C NMR (100 MHz, CDCl₃, ppm): 149.88; 142.16; 135.03; 131.17; 123.45; 112.88; 63.19.

[0064] Triphenylmethyl-(4-bromo-3-nitrobenzyl)ether (3)²⁰: In a 1 L flask, compound 2 (42.0 g, 0.18 mol), trityl chloride (56.0 g, 0.20 mol, Aldrich Co.), dimethylaminopyridine (0.89 g, 7.30 mmol, Aldrich Co.), triethylamine (46 mL, Aldrich Co.) and dichloromethane (400 mL) were mixed and stirred for 24 h. Distilled water (250 mL) was added and the organic layer was washed two times with a saturated NH₄Cl solution followed by water. The combined organic fractions were dried over magnesium sulfate and the solvent was removed under reduced pressure. The crude material was recrystallized in ethanol to provide 76.4 g of the title product as a yellow crystalline solid. M.P.: 148-150°C (Yield: 89%). ¹H NMR (400 MHz, CDCl₃, ppm): 7.83 (s, 1H); 7.69 (d, 1H, *J* = 8.3 Hz); 7.53 (d, 1H, *J* = 7.2 Hz); 7.34 (m, 15H); 4.29 (s, 2H). ¹³C NMR (100 MHz, CDCl₃, ppm): 149.98; 143.57; 140.62; 134.81; 131.46; 128.64; 128.14; 127.45; 123.79; 112.55; 87.71; 64.33.

[0065] Triphenylmethyl-(4-bromobenzyl)ether (4)¹⁹: In a 1 L flask, 4-bromobenzyl alcohol (50.0 g, 0.27 mol, Aldrich Co.), trityl chloride (82.0 g, 0.29 mol, Aldrich Co.), dimethylaminopyridine (1.31 g, 10.6 mmol, Aldrich Co.), triethylamine (67 mL, Aldrich Co.) and dichloromethane (550 mL) were mixed and

stirred for 24 h. Distilled water (300 mL) was added and the organic layer was washed two times with a saturated NH_4Cl solution followed by water. The combined organic fractions were dried over magnesium sulfate and the solvent was removed under reduced pressure. The crude material was recrystallized in ethanol to provide 111 g of the title product as a white crystalline solid. M.P.: 149-150°C (Yield: 96%). ^1H NMR (300 MHz, CDCl_3 , ppm): 7.59 (d, 2H, $J = 7.4$ Hz); 7.53 (d, 2H, $J = 8.4$ Hz); 7.35 (m, 15H); 4.23 (s, 2H). ^{13}C NMR (75 MHz, CDCl_3 , ppm): 144.06; 138.24; 131.46; 128.78 (2C); 128.03; 127.25; 121.00; 87.27; 65.26.

[0066] Triphenylmethyl-(4-(dimethoxyborane)benzyl)ether (5): To a solution of compound 4 (50.0 g, 0.12 mol) in anhydrous THF (500 mL) was added dropwise *n*-butyllithium (51.7 mL, 0.13 mol, 2.5 M in hexanes, Aldrich Co.) at -78°C under argon. The mixture was stirred 2 h at -78°C during which the solution turned pink followed by the formation of a white precipitate. Trimethylborate (26.4 mL, 0.24 mol, Aldrich Co.) was then added dropwise and the solution turned clear. The mixture was stirred at -78°C for an additional hour followed by 16 h at room temperature. The solution was then quenched with an aqueous saturated NaHCO_3 solution (550 mL). Diethyl ether (500 mL) was added and the organic layer was washed three times with water (200 mL) followed by brine (200 mL). The combined organic fraction was dried over magnesium sulfate and the solvent was removed under reduced pressure to give a colorless oil that was used in the next step without further purification.

[0067] 4,4'-bis(trityloxymethyl)-2-nitrobiphenyl (6): In a 250 mL flask, compound 3 (42.4 g, 89.4 mmol), compound 5 (39.7 g, 94.0 mmol), toluene (200 mL) and aqueous K_2CO_3 (2 M, 75 mL) were mixed. The resulting solution was degassed with a vigorous flow of argon for 1 h. Palladium (II) acetate (0.42 g, 1.88 mmol, Aldrich Co.) and triphenylphosphine (1.98 g, 7.52 mmol, Aldrich Co.) were then added and the mixture was refluxed for 16 h under argon. The mixture was cooled at room temperature and the white precipitate was filtered through a

Büchner funnel. The resulting solid was washed thoroughly with water followed by methanol and dried under reduced pressure to provide 65.8 g of the title product as a white solid. M.P.: 250-251°C (Yield: 85%). ¹H NMR (300 MHz, CDCl₃, ppm): 7.87 (s, 1H); 7.58 (m, 14H); 7.38 (m, 22H); 4.36 (s, 2H); 4.30 (s, 2H). ¹³C NMR (75 MHz, CDCl₃, ppm): 149.32; 144.11; 143.73; 140.08; 139.37; 136.06; 134.82; 131.87; 130.53; 128.80; 128.71; 128.10; 127.97; 127.90; 127.37; 127.21; 127.16; 122.36; 87.58; 87.15; 65.40; 64.67.

[0068] 2,7-bis(trityloxymethyl)carbazole (7): In a 500 mL flask, compound 6 (40.0 g, 54.2 mmol) and triethylphosphite (250 mL) were mixed and refluxed under argon for 12 h. The mixture was cooled at 0°C and the precipitate was filtered through a Büchner funnel. The solid was washed thoroughly with methanol and dried under reduced pressure to provide 23.0 g of the title product as a white solid. M.P.: 240°C (dec.) (Yield: 60 %). ¹H NMR (400 MHz, THF-*d*₆, ppm): 10.24 (s, 1H); 7.94 (d, 2H, *J* = 8.0 Hz); 7.53 (m, 14H); 7.28 (m, 12H); 7.20 (m, 6H); 7.08 (dd, 2H, *J* = 8.0 and 1.4 Hz); 4.30 (s, 4H). The ¹³C NMR experiment could be performed on this compound due to its very low solubility in common deuterated solvents.

[0069] *N*-(2-ethylhexyl)-2,7-bis(trityloxymethyl)carbazole (8)⁹: A 250 mL flask was charged with compound 7 (20.0 g, 28.4 mmol), sodium hydroxide (2.28 g, 56.8 mmol), tetrabutylammonium hydrogensulfate (0.48 g, 1.42 mmol), 2-ethylhexylbromide (11.0 g, 57.0 mmol, Aldrich Co.) and anhydrous acetone (140 mL). The resulting mixture was refluxed under argon for 24 h and then cooled at room temperature. Water (300 mL) was then added under vigorous stirring and the white precipitate formed was collected by filtration. The solid was dissolved in a small amount of acetone and poured into methanol at 0°C. The precipitate was filtered and rinsed thoroughly with methanol to provide 21.6 g of the title product as a white solid. M.P.: 180-182°C (Yield: 93 %). ¹H NMR (300 MHz, CDCl₃, ppm): 8.15 (d, 2H, *J* = 8.0 Hz); 7.74 (d, 12H, *J* = 7.6 Hz); 7.68 (s, 2H); 7.46 (m, 12H);

7.39 (m, 6H); 7.31 (d, 2H, $J = 8.0$ Hz); 4.55 (s, 4H); 4.34 (m, 2H); 2.30 (m, 1H); 1.47 (m, 8H); 1.11 (t, 3H, $J = 7.2$ Hz); 0.94 (t, 3H, $J = 6.8$ Hz). ^{13}C NMR (75 MHz, CDCl_3 , ppm): 144.46; 141.55; 136.86; 128.97; 128.02; 127.20; 122.03; 120.02; 118.12; 107.57; 87.25; 66.66; 39.60; 31.21; 28.92; 28.56; 24.56; 23.24; 14.17; 11.14.

[0070] *N*-hexyl-2,7-bis(trityloxymethyl)carbazole (9)⁹: This product was obtained (via compound 7) following the same procedure as used for the synthesis of compound 8 using 1-bromohexane instead of 2-ethylhexylbromide to provide the title product as a white solid. M.P.: 183-184°C (Yield: 90 %). ^1H NMR (300 MHz, CDCl_3 , ppm): 8.13 (d, 2H, $J = 8.0$ Hz); 7.71 (d, 12H, $J = 7.6$ Hz); 7.56 (s, 2H); 7.44 (m, 12H); 7.36 (m, 8H); 4.52 (s, 4H); 4.39 (t, 2H, $J = 7.0$ Hz); 2.00 (m, 2H); 1.48 (m, 6H); 0.96 (t, 3H, $J = 6.8$ Hz). ^{13}C NMR (75 MHz, CDCl_3 , ppm): 144.44; 141.00; 136.84; 128.96; 128.01; 127.18; 122.07; 120.11; 118.21; 107.35; 87.26; 66.72; 43.23; 31.76; 29.11; 27.18; 22.72; 14.18.

[0071] *N*-(2-ethylhexyl)-2,7-bis(hydroxymethyl)carbazole (10): A 500 mL flask was charged with compound 8 (20.0 g, 24.6 mmol), dichloromethane (500 mL), methanol (100 mL) and concentrated HCl (2 mL). The resulting mixture was stirred for 2 h, which was followed by the addition of saturated aqueous NaHCO_3 (200 mL). The aqueous layer was removed and the organic layer was washed three times with distilled water (200 mL). The combined organic layer was dried over magnesium sulfate and the solvent was removed under reduced pressure. The resulting solid was recrystallized twice in toluene to provide 6.44 g of the title product as a white solid. M.P.: 119-120°C (Yield: 81 %). ^1H NMR (300 MHz, Acetone- d_6 , ppm): 8.04 (d, 2H, $J = 8.0$ Hz); 7.55 (s, 2H); 7.18 (d, 2H, $J = 7.9$); 4.83 (s, 2H); 4.82 (s, 4H); 4.28 (m, 2H); 2.13 (m, 1H); 1.40 (m, 6H); 1.25 (m, 2H); 0.92 (t, 3H, $J = 7.4$ Hz); 0.84 (t, 3H, $J = 7.2$ Hz). ^{13}C NMR (75 MHz, Acetone- d_6 , ppm): 142.14; 140.98; 122.39; 120.34; 118.45; 107.93; 65.32; 47.59; 39.89; 31.43; 29.18; 24.83; 23.58; 14.11; 11.10.

[0072] N-hexyl-2,7-bis(hydroxymethyl)carbazole (11): This product was obtained (via compound 9) following the same procedure as used for the synthesis of compound 10 to provide the title product as a white solid. M.P.: 96-97°C (Yield: 87 %). ¹H NMR (400 MHz, Acetone-d₆, ppm): 8.03 (d, 2H, *J* = 8.0 Hz); 7.55 (s, 2H); 7.18 (d, 2H, *J* = 7.9 Hz); 4.83 (d, 4H, *J* = 5.8 Hz); 4.36 (t, 2H, *J* = 7.3 Hz); 4.31 (t, 2H, *J* = 5.8 Hz); 1.85 (m, 2H); 1.34 (m, 6H); 0.85 (t, 3H, *J* = 7.1 Hz). ¹³C NMR (100 MHz, Acetone-d₆, ppm): 141.12; 140.43; 121.86; 119.85; 117.93; 107.14; 64.80; 42.69; 31.69; 29.02; 26.81; 22.59; 13.63.

[0073] N-(2-ethylhexyl)-2,7-bis(formyl)carbazole (12)²¹: In a 250 mL flask, compound 10 (5.00 g, 14.8 mmol), pyridinium chlorochromate (PCC) (12.8 g, 59.3 mmol, Aldrich Co.), dry molecular sieves 4Å (2.50 g, Aldrich Co.) and silica gel (2.50 g) were added to dichloromethane (150 mL) at 0°C. The resulting mixture was stirred 2 h at room temperature and then filtered over silica gel (dichloromethane as eluent) to provide the title product as a bright yellow solid. M.P.: 120-121°C (Yield: 76 %). ¹H NMR (300 MHz, CDCl₃, ppm): 10.14 (s, 2H); 8.20 (d, 2H, *J* = 8.01 Hz); 7.90 (s, 2H); 7.74 (d, 2H, *J* = 8.04 Hz); 4.20 (d, 2H, *J* = 7.6 Hz); 2.06 (s, 1H); 1.29 (m, 8H); 0.89 (t, 3H, *J* = 7.4 Hz); 0.82 (t, 3H, *J* = 6.8 Hz). ¹³C NMR (75 MHz, CDCl₃, ppm): 192.24; 142.13; 135.16; 126.75; 121.70; 121.18; 110.62; 47.84; 39.38; 30.81; 28.54; 24.34; 22.97; 13.94; 10.84.

[0074] N-hexyl-2,7-bis(formyl)carbazole (13)²¹: This product was obtained (via compound 11) following the same procedure as used for the synthesis of compound 12 to provide the title product as a bright yellow solid. M.P.: 98-99°C (Yield: 76 %). ¹H NMR (400 MHz, CDCl₃, ppm): 10.16 (s, 2H); 8.22 (d, 2H, *J* = 8.4 Hz); 7.95 (s, 2H); 7.75 (dd, 2H, *J* = 8.0 and 0.9 Hz); 4.36 (t, 2H, *J* = 7.4 Hz); 1.88 (m, 2H); 1.34 (m, 6H); 0.84 (t, 3H, *J* = 7.0 Hz). ¹³C NMR (100 MHz, CDCl₃, ppm): 192.56; 141.87; 135.34; 127.00; 121.96; 121.55; 110.44; 43.77; 31.68; 29.29; 27.08; 22.72; 14.18.

[0075] ***N*-(2-ethylhexyl)-2,7-bis(acetonitrile)carbazole (14)²²:** To a solution of potassium *tert*-butoxide (7.23 g, 67.1 mmol, Aldrich Co.) in THF (150 mL) was slowly added under argon a solution of tosylmethyl isocyanide (6.26 g, 32.0 mmol, Aldrich Co.) in anhydrous THF (50 mL). The resulting mixture was cooled at -30°C and a solution containing compound 12 (5.00 g, 14.9 mmol) in anhydrous THF (50 mL) was slowly added. The mixture was stirred at -30°C for 45 minutes followed by the addition of MeOH (200 mL). The solution was heated at 80°C for 15 minutes and cooled at room temperature. The solvent was removed under reduced pressure and 10 mL of glacial acetic acid was added to the resulting dark solid. Water (100 mL) was added and the solid washed three times with dichloromethane. The combined organic layer was dried over magnesium sulfate and the solvent was removed under reduced pressure. The crude dark red viscous oil was purified by column chromatography (silica gel, 30 % ethyl acetate in hexanes as eluent) to provide the title product as a slightly yellow solid. M.P.: 79-80°C (Yield: 29 %). ¹H NMR (300 MHz, CDCl₃, ppm): 8.01 (d, 2H, *J* = 8.0 Hz); 7.32 (s, 2H); 7.13 (d, 2H, *J* = 8.0 Hz); 4.04 (m, 2H); 3.95 (s, 4H); 2.02 (m, 1H); 1.33 (m, 8H); 0.80 (m, 6H). ¹³C NMR (75 MHz, CDCl₃, ppm): 141.50; 127.72; 122.03; 120.99; 119.02; 118.35; 108.55; 47.37; 39.31; 30.92; 28.69; 24.38; 24.26; 23.06; 14.03; 10.94.

[0076] ***N*-(2-ethylhexyl)-2,7-bis(chloromethyl)carbazole (15):** To a solution of compound 10 (5.00 g, 14.8 mmol) in dry toluene (140 mL) containing a few drops of pyridine was slowly added thionyl chloride (6.48 mL, 88.9 mmol, Aldrich Co.) at 0°C. The mixture was stirred at 0°C for 1h and at room temperature for 2h. The excess thionyl chloride and toluene were removed under reduced pressure. The crude product was purified by column chromatography (silica gel, 10 % ethyl acetate in hexanes as eluent). The yellow oil obtained was decolorized using activated carbon to provide 3.82 g of the title product as a slightly yellow solid. (Yield: ~85 %). (The final product contained 5-10 % of unknown impurities : and was used as is).

[0077] ***N*-hexyl-2,7-bis(chloromethyl)carbazole (16):** This product was obtained (via compound 11) following the same procedure as used for the synthesis of compound 15 to provide the title product as a slightly yellow solid. (Yield: ~82 %). (The final product contained 5-10 % of unknown impurities and was used as is).

[0078] ***N*-(2-ethylhexyl)-2,7-bis(methylphosphonate)carbazole (17):** In a 100 mL flask, compound 15 (3.80 g, 12.5 mmol) and triethylphosphite (50 mL) were mixed and heated to reflux under argon for 24 h. The excess triethylphosphite was removed under reduced pressure and the crude product was purified by column chromatography (silica gel, 50 % acetone in hexanes as eluent) to provide 4.86 g of the title product as a yellow waxy solid. M.P.: 70-71°C (Yield: 83 %). ¹H NMR (300 MHz, CDCl₃, ppm): 7.89 (d, 2H, *J* = 8.0 Hz); 7.26 (s, 2H); 7.06 (d, 2H, *J* = 7.9 Hz); 4.06 (m, 2H); 3.92 (m, 8H); 3.28 (d, 4H, *J* = 21.3 Hz); 1.99 (m, 1H); 1.27 (m, 8H); 1.15 (t, 12H, *J* = 7.0 Hz); 0.79 (m, 6H). ¹³C NMR (75 MHz, CDCl₃, ppm): 141.33; 128.92; 128.80; 121.48; 120.83; 120.76; 120.06; 110.19; 110.10; 62.05; 61.97; 47.45; 39.20; 35.37; 33.54; 30.94; 28.76; 24.31; 22.96; 16.38; 16.31; 13.94; 10.90.

[0079] - ***N*-hexyl-2,7-bis(methylphosphonate)carbazole (18):** This product was obtained (via compound 16) following the same procedure as used for the synthesis of compound 17. The crude product was purified by column chromatography (silica gel, 50 % acetone in hexanes as eluent) to provide the title product as a white solid. M.P.: 117-119°C (Yield: 80 %). ¹H NMR (400 MHz, CDCl₃, ppm): 7.97 (d, 2H, *J* = 7.9 Hz); 7.35 (s, 2H); 7.12 (d, *J* = 7.9 Hz); 4.26 (t, 2H, *J* = 7.3 Hz); 3.99 (m, 8H); 3.36 (d, 4H, *J* = 21.5 Hz); 1.84 (m, 2H); 1.34 (m, 6H); 1.23 (t, 12H, *J* = 7.0 Hz); 0.85 (t, 3H, *J* = 6.9 Hz). ¹³C NMR (100 MHz, CDCl₃, ppm): 141.11; 129.16; 126.06; 121.76; 121.06; 121.00; 120.40; 110.15; 110.07; 62.37; 62.30; 43.36; 35.40; 33.99; 31.86; 29.17; 27.16; 22.75; 16.65; 16.59; 14.24.

[0080] *N*-(2-ethylhexyl)-2,7-bis(methyltriphenylphosphonium

chloride)carbazole (19): In a 100 mL flask, compound 15 (3.00 g, 7.98 mmol), triphenylphosphine (5.23 g, 19.9 mmol) and anhydrous DMF (80 mL) were stirred at 120°C under argon for 24 h. The mixture was cooled at room temperature and poured in 300 mL of cold diethyl ether under vigorous stirring. The slightly yellow precipitate was filtered and washed thoroughly with diethyl ether. The solid was dissolved in water and extracted five times with dichloromethane. The combined organic fractions were dried over magnesium sulfate and the solvent was removed under reduced pressure to provide 5.13 g of the title product as a slightly yellow solid. M.P. >260°C (Yield: 71 %). ¹H NMR (400 MHz, CDCl₃, ppm): 7.91 (m, 10H); 7.72 (m, 22H); 7.21 (s, 2H); 6.83 (m, 2H); 5.20 (d, 4H, *J* = 14.7 Hz); 3.80 (m, 2H); 1.44 (m, 1H); 0.95 (m, 8H); 0.78 (t, 3H, *J* = 6.7 Hz); 0.71 (t, 3H, *J* = 7.3 Hz). ¹³C NMR (100 MHz, CDCl₃, ppm): 141.37; 135.30; 134.34; 130.26; 125.38; 122.42; 120.83; 118.69; 117.80; 111.93; 53.87; 38.38; 30.64; 30.47; 29.99; 29.69; 28.67; 24.29; 22.90.

[0081] *N*-(2-ethylhexyl)-2,7-divinylcarbazole (20): In a 100 mL flask,

compound 12 (2.00 g, 5.96 mmol), sodium hydride (0.36 mg, 14.9 mmol, Aldrich Co.), methyl triphenylphosphonium bromide (5.11g, 14.3 mmol, Aldrich Co.) and anhydrous THF (60 mL) were heated to reflux under argon for 2h. The resulting solution was cooled at room temperature and methanol (50 mL) was slowly added followed by water (50 mL). The aqueous layer was washed three times with dichloromethane (100 mL) and the combined organic fractions were washed with brine followed by water. The organic layer was dried over magnesium sulfate and the solvent was removed under reduced pressure. The crude product was purified by column chromatography (5 % ethyl acetate in hexanes as eluent) to provide 1.80 g of the title product as a pale yellow solid. M.P.: 59-60°C (Yield: 92 %). ¹H NMR (400 MHz, CDCl₃, ppm): 8.03 (d, 2H, *J* = 7.9 Hz); 7.39 (m, 4H); 6.98 (dd, 2H, *J* = 8.2 Hz and 6.6 Hz); 5.95 (d, 2H, *J* = 0.9 Hz); 5.90 (d, 2H, *J* = 0.9 Hz); 4.13 (m, 2H); 2.11 (m, 1H); 1.40 (m, 8H); 0.98 (m, 6H). ¹³C NMR (100 MHz, CDCl₃, ppm):

142.06; 138.17; 135.57; 122.81; 120.50; 117.66; 113.31; 107.15; 47.38; 39.62;
31.20; 29.02; 24.73; 23.34; 14.37; 11.23.

[0082] ***N*-(4-octyloxyphenyl)-2,7-bis(hydroxymethyl)carbazole (21):** In a
50 mL flask, compound 7 (6.00 g, 8.52 mmol), 4-octyloxy-1-iodobenzene (3.40 g,
5 10.2 mmol), potassium hydroxide (3.20g, 57.1 mmol), copper (I) chloride (67 mg,
0.68 mmol, Aldrich Co.), 1,10-phenanthroline (67 mg, 0.37 mmol) and toluene (25
mL) were mixed and refluxed for 24 h. The mixture was cooled at room
temperature and poured into water. The aqueous layer was extracted three times
with dichloromethane and the combined organic layers were dried over
10 magnesium sulfate. The solvent was removed under reduced pressure and the
resulting crude product was dissolved in a mixture of dichloromethane (250 mL)
and methanol (75 mL) containing a few drops of concentrated HCl (1 mL). The
resulting mixture were stirred for 2 h followed by the addition of saturated aqueous
NaHCO₃ (100 mL). The aqueous layer was removed and the organic layer was
15 washed three times with distilled water (100 mL). The combined organic layers
were dried over magnesium sulfate and the solvent was removed under reduced
pressure. During evaporation, a white precipitate was formed which was
subsequently separated from solution by filtration. This process was repeated until
a precipitate was no longer formed. The combined precipitates were dried under
20 reduced pressure to provide 2.89 g of the title product as a white solid (Yield: 94
%). ¹H RMN (400 MHz, Acetone-d₆, ppm): 8.10 (d, 2H, J = 8.0 Hz); 7.48 (d, 2H, J
= 8.9 Hz); 7.34 (s, 2H); 7.23 (m, 4H); 4.76 (d, 4H, J = 5.9 Hz); 4.22 (t, 2H, J = 5.8
Hz); 4.14 (t, 2H, J = 6.5 Hz); 1.86 (m, 2H); 1.55 (m, 2H); 1.38 (m, 8H); 0.91 (t, 3H,
J = 7.0 Hz). ¹³C RMN (100 MHz, Acetone-d₆, ppm): 158.92; 142.04; 140.90;
25 130.17; 128.81; 122.12; 119.89; 118.80; 115.86; 107.69; 68.28; 64.53; 31.91;
29.42; 29.36; 26.14; 22.65; 13.69.

[0083] ***N*-(4-octyloxyphenyl)-2,7-bis(formyl)carbazole (22):** In a 100 mL
flask, compound 21 (1.50 g, 3.48 mmol), pyridinium chlorochromate (3.75 g, 17.4

mmol, Aldrich Co.), molecular sieves 4Å (750 mg), silica gel (750 mg) and dichloromethane (35 mL) were mixed at room temperature. The resulting mixture was stirred at room temperature for 2h and then filtered onto silica gel (dichloromethane as eluent) to provide the title product as a bright yellow solid.

M.P.: (Yield: 99 %). ¹H RMN (400 MHz, CDCl₃, ppm): 10.08 (s, 2H); 8.29 (d, 2H, J = 8.1 Hz); 7.86 (s, 2H); 7.83 (dd, 4H, J = 8.0 and 1.3 Hz); 7.41 (d, 2H, J = 8.9 Hz); 7.14 (d, 2H, J = 8.9 Hz); 4.08 (t, 2H, J = 6.6 Hz); 1.87 (m, 2H); 1.53 (m, 2H); 1.36 (m, 8H); 0.91 (t, 3H, J = 6.8 Hz). ¹³C RMN (100 MHz, CDCl₃, ppm): 192.46; 159.57; 143.00; 135.60; 128.78; 128.45; 121.95; 121.74; 121.12; 116.27; 112.32; 68.71; 32.06; 29.59; 29.50; 29.45; 26.30; 22.90; 14.36.

[0084] 4-methyltrityloxy-2-nitrobiphenyl (23): In a 500 mL flask, compound 3 (55.0 g, 117 mmol), phenylboronic acid (15.0 g, 123 mmol, Aldrich Co.), toluene (180 mL) and aqueous K₂CO₃ 2 M (70 mL) were mixed. The resulting solution was degassed with a vigorous flow of argon for 1 h. Palladium (II) acetate (0.55 g, 2.46 mmol, Aldrich Co.) and triphenylphosphine (2.58 g, 9.84 mmol, Aldrich Co.) were then added and the mixture was refluxed for 16 h under argon. The mixture was cooled at room temperature and water (200 mL) was added. The aqueous layer was washed three times with toluene (100 mL) and the combined organic fractions were dried with magnesium sulfate. The residue was filtered and the filtrate was decolorized by heating in presence of activated carbon followed by filtration on Celite®. The solvent was removed under reduced pressure and the crude product was purified by precipitation in ethanol to provide 51.9 g of the title product as a white solid. M.P.: 113-115°C (Yield: 95%). ¹H NMR (400 MHz, CDCl₃, ppm): 7.88 (m, 1H); 7.63 (m, 1H); 7.58 (m, 3H); 7.56 (m, 3H); 7.44 (m, 4H); 7.38 (m, 8H); 7.31 (m, 3H); 4.36 (s, 2H). ¹³C NMR (100 MHz, CDCl₃, ppm): 149.44; 143.90; 140.35; 137.58; 135.17; 132.05; 130.76; 128.94; 128.88; 128.42; 128.30; 128.19; 127.57; 122.55; 87.75; 64.84.

[0085] 2-methyltrityloxycarbazole (24): In a 500 mL flask, compound **23** (51.5 g, 110 mmol) and triethylphosphite (275 mL) were mixed and refluxed under argon for 12 h. The mixture was cooled at room temperature and excess triethylphosphite was removed under reduced pressure. Methanol (250 mL) was added and the precipitate was filtered through a Büchner funnel. The white precipitate was recrystallized in an ethyl acetate/hexanes mixture to provide 31.0 g of the title product as a white solid. M.P.: 228-230°C (Yield: 65 %). ¹H NMR (300 MHz, CDCl₃, ppm): 10.34 (s, 1H); 8.09 (m, 2H); 7.65 (m, 1H); 7.60 (m, 3H); 7.58 (m, 3H); 7.52 (m, 1H); 7.37 (m, 7H); 7.29 (m, 3H); 7.17 (m, 2H); 4.34 (s, 2H). ¹³C NMR (75 MHz, CDCl₃, ppm): 144.58; 140.57; 140.51; 136.94; 128.86; 128.07; 127.29; 125.60; 123.22; 122.50; 120.13; 120.06; 119.02; 118.38; 111.04; 109.59; 87.18; 86.45.

[0086] N-hexyl-2-hydroxymethylcarbazole (25): A 500 mL flask was charged with compound **24** (20.0 g, 45.9 mmol), sodium hydroxide (3.67 g, 91.8 mmol), tetrabutylammonium hydrogensulfate (0.78 g, 2.29 mmol), 1-bromohexane (15.2 g, 91.8 mmol, Aldrich Co.) and anhydrous acetone (230 mL). The resulting mixture was refluxed under argon for 24 h and then poured into 250 mL of distilled water. The aqueous layer was extracted three times with diethyl ether (100 mL). The combined organic fractions were dried over magnesium sulfate and the solvent was removed under reduced pressure to give an orange oil. The crude product was dissolved in dichloromethane (500 mL) and methanol (100 mL). Concentrated hydrochloric acid (2 mL) was added and the mixture was stirred for 30 minutes at room temperature. Saturated aqueous NaHCO₃ (200 mL) was then added. The aqueous layer was removed and the organic layer was extracted three times with distilled water (100 mL). The combined organic layer were dried over magnesium sulfate and the solvent was removed under reduced pressure. The residue was purified by column chromatography (30% ethyl acetate in hexanes as eluent) to provide 11.7 g of the title product as a white solid. M.P.: 54-55°C (Yield: 90 %). ¹H NMR (300 MHz, CDCl₃, ppm): 8.09 (t, 2H, J = 8.5 Hz); 7.43

(m, 3H); 7.23 (m, 2H); 4.89 (s, 2H); 4.28 (t, 2H, $J = 7.4$ Hz); 1.93 (s, 1H); 1.87 (m, 2H); 1.36 (m, 6H); 0.89 (t, 3H, $J = 6.9$ Hz). ^{13}C NMR (75 MHz, Acetone- d_6 , ppm): 141.54; 141.50; 141.29; 126.09; 123.56; 122.52; 120.79; 120.66; 119.45; 118.60; 109.70; 107.75; 65.47; 43.30; 32.25; 29.60; 27.43; 23.18; 14.29.

- 5 [0087] ***N*-hexyl-2-formylcarbazole (26):** In a 250 mL flask, compound 25 (2.00 g, 7.11 mmol), pyridinium chlorochromate (PCC) (3.06 g, 14.2 mmol, Aldrich Co.), dry molecular sieves 4Å (1.20 g, Aldrich Co.) and silica gel (1.20 g) were added to dichloromethane (70 mL) at 0°C. The resulting mixture was stirred 2 h at room temperature and then filtered onto silica gel (dichloromethane as eluent) to provide 1.79 g of the title product as an orange oil (Yield: 90 %). ^1H NMR (300 MHz, CDCl_3 , ppm): 10.15 (s, 1H); 8.14 (m, 2H); 7.92 (s, 1H); 7.71 (d, 1H, $J = 8.0$ Hz); 7.55 (t, 1H, $J = 7.3$ Hz); 7.41 (d, 1H, $J = 8.3$ Hz); 7.27 (t, 1H, $J = 7.4$ Hz); 4.27 (t, 2H, $J = 7.4$ Hz); 1.85 (m, 2H); 1.30 (m, 6H); 0.88 (t, 3H, $J = 6.5$ Hz). ^{13}C NMR (75 MHz, CDCl_3 , ppm): 192.63; 142.21; 140.06; 133.85; 128.08; 127.60; 121.92; 121.45; 121.18; 120.52; 119.59; 109.64; 109.22; 43.26; 31.55; 29.00; 26.93; 22.56; 14.03.

- [0088] ***N*-hexyl-2-chloromethylcarbazole (27):** To a solution of compound 25 (5.00 g, 14.8 mmol) in dry toluene (140 mL) containing a few drops of pyridine, was slowly added thionyl chloride (6.48 mL, 88.9 mmol, Aldrich Co.) at 0°C. The mixture was stirred at 0°C for 1h and at room temperature for 2h. Excess thionyl chloride and toluene were removed under reduced pressure. The crude product was purified by column chromatography (silica gel, 10 % ethyl acetate in hexanes as eluent). The yellow oil obtained was decolorized using activated carbon to provide 3.82 g of the title product as a slightly yellow solid (Yield: ~87 %). (The final product contained 5-10 % of unknown impurities and was used as is).

[0089] ***N*-hexyl-2-methylphosphonatecarbazole (28):** In a 250 mL flask, compound 27 (10.0 g, 33.3 mmol) and triethylphosphite (125 mL) were mixed and

heated to reflux under argon for 24 h. The solution was cooled to room temperature and excess triethylphosphite was removed under reduced pressure. The resulting orange solution was purified by column chromatography (40 % acetone in hexanes as eluent) to provide 8.40 g of the title product as a yellow viscous oil (Yield: 63 %). ¹H NMR (300 MHz, CDCl₃, ppm): 8.08 (d, 1H, *J* = 7.8 Hz); 8.03 (d, 1H, *J* = 8.0 Hz); 7.46 (m, 1H); 7.38 (m, 2H); 7.23 (m, 1H); 7.16 (m, 1H); 4.28 (t, 2H, *J* = 6.5 Hz); 4.02 (m, 4H); 3.38 (d, 2H, *J* = 21.5 Hz); 1.86 (m, 2H); 1.34 (m, 6H); 1.24 (t, 6H, *J* = 7.3 Hz); 0.88 (t, 3H, *J* = 7.0 Hz). ¹³C NMR (75 MHz, CDCl₃, ppm): 140.86; 129.21; 129.12; 129.12; 125.74; 122.85; 122.83; 121.98; 121.95; 121.01; 120.94; 120.52; 120.50; 120.44; 119.03; 110.13; 110.06; 108.93; 62.39; 62.33; 43.29; 35.40; 34.03; 31.85; 29.16; 27.18; 22.78; 16.68; 16.62; 14.26.

[0090] 4-Hexyl-4'-trityloxymethyl-2'-nitro-1,1'-biphenyl (29): In a 500 mL flask, 4-hexylphenylboronic acid (21.36 g, 104 mmol), 4-bromo-3-nitro(trityloxymethyl)benzene (46.3 g, 98 mmol), toluene (250 mL) and an aqueous solution of potassium carbonate 2 M (100 mL) were mixed. The resulting solution was degassed with a vigorous argon flow for 1 h. Palladium acetate (0.47 g, 2.10 mmol, Aldrich Co.) and triphenylphosphine (2.17 g, 8.40 mmol, Aldrich Co.) were then added and the solution was refluxed for 16 h under argon atmosphere. The solution was cooled at room temperature and distilled water (150 mL) was added. The organic layer was separated, washed three times with distilled water and dried over magnesium sulfate. The solvent was removed providing a yellow viscous oil. The organic layer was separated and washed three times with distilled water. Hot methanol (300 mL) was then added. The resulting mixture was stirred while being cooled in an ice/water bath. The obtained yellow precipitate was collected by filtration and dried under reduced pressure for 24 h to provide 33.9 g of the title product as a white powder. M.P.: 86-87°C (Yield = 84 %). ¹H NMR (400MHz, CDCl₃, ppm): 7.84 (s, 1H); 7.61 (d, 1H, *J* = .8 Hz); 7.58 (m, 2H); 7.56 (m, 4H); 7.43 (d, 1H, *J* = 7.9 Hz); 7.37 (m, 6H); 7.32 (m, 3H); 7.28 (m, 4H); 4.35 (s, 2H); 2.70 (t, 2H, *J* = 8.2 Hz); 1.70 (m, 2H); 1.39 (m, 6H); 0.95 (t, 3H, *J* = 7.2 Hz). ¹³C NMR (100

MHz, CDCl₃, ppm): 149.54; 143.91; 143.35; 140.01; 135.13; 134.69; 132.03; 130.65; 129.01; 128.88; 128.28; 128.03; 127.55; 122.48; 87.72; 64.85; 35.97; 31.99; 31.56; 29.33; 22.88; 14.40.

[0091] **2-Hexyl-7-(trityloxymethyl)carbazole (30):** In a 250 mL flask, compound **29** (32.0 g, 58.0 mmol) and triethylphosphite (150 mL, Aldrich Co.) were mixed. The resulting solution was refluxed for 16 h under argon atmosphere. Excess triethylphosphite was removed under reduced pressure. Ethanol (250 mL) was then added under vigorous stirring leading to a white precipitate. The solid was collected by filtration, rinsed thoroughly with methanol and dried under reduced pressure for 24 h to provide the title product as a white powder. M.P.: 155-156°C (Yield: 67 %). ¹H NMR (400MHz, CDCl₃, ppm): 8.03 (t, 2H, J = 6.5 Hz); 7.82, (s, 1H); 7.68 (m, 6H); 7.54 (s, 1H); 7.41 (m, 6H); 7.33 (m, 3H); 7.24 (m, 2H); 7.15 (dd, 1H, J = 8.0 et 1.3 Hz); 4.43 (s, 2H); 7.84 (t, 2H, J = 8.0 Hz); 1.78 (m, 2H); 1.43 (m, 6H); 1.00 (t, 3H, J = 7.0 Hz). ¹³C NMR (100 MHz, CDCl₃, ppm): 144.56; 141.29; 140.41; 140.01; 136.82; 129.09; 128.20; 127.36; 122.82; 121.48; 120.65; 120.16; 119.98; 118.83; 110.42; 109.25; 87.37; 66.61; 36.86; 32.27; 32.12; 29.40; 22.98; 14.48.

[0092] **N-methyl-2-hexyl-7-(hydroxymethyl)carbazole (31):** To a solution of compound **30** (19.33 g, 37.4 mmol) in anhydrous acetone (200 mL) were added sodium hydroxide (2.98 g, 74.5 mmol), tetrabutylammonium hydrogensulfate (0.39 g, 1.12 mmol) and iodomethane (10.6 g, 74.5 mmol). The resulting solution was refluxed for 4 h and then cooled to room temperature. Acetone was removed under reduced pressure and diethyl ether (250 mL) and distilled water (200 mL) were added. The organic layer was separated and washed two times with distilled water. The solvent was removed under reduced pressure and the resulting white solid was dissolved in a mixture of dichloromethane (400 mL) and methanol (100 mL) containing few drops of concentrated HCl. The resulting mixture was stirred for 1 h and a saturated aqueous sodium bicarbonate solution (250 mL) was added.

The organic layer was separated, dried over magnesium sulfate and removed under reduced pressure. The crude was purified by column chromatography (silica gel, 30 % ethyl acetate in hexanes as eluent) to provide 9.43 g of the title product as a white solid. M.P.: 90-91°C (Yield: 87 %). ¹H NMR (400MHz, CDCl₃, ppm): 8.00 (d, 2H, *J* = 7.9 Hz); 7.32 (s, 1H); 7.16 (m, 3H); 4.84 (s, 2H); 3.70 (s, 3H); 2.88 (t, 2H, *J* = 7.7 Hz); 2.51 (s, 1H); 1.81 (m, 2H); 1.45 (m, 6H); 1.00 (t, 3H, *J* = 7.1 Hz). ¹³C NMR (100 MHz, CDCl₃, ppm): 141.95; 141.52; 141.36; 138.45; 122.58; 120.76; 120.19; 120.14; 120.10; 118.14; 108.28; 107.10; 66.22; 37.12; 32.43; 32.13; 29.49; 29.08; 22.98; 14.47.

[0093] N-methyl-2-hexyl-7-chloromethylcarbazole (32): To a solution of compound **31**. (2.00 g, 6.89 mmol) in anhydrous toluene (140 mL) at 0°C was added thionyl chloride (1.64 g, 13.9 mmol). The resulting solution was stirred at 0°C for 1 h and then for 2 h at room temperature. Excess thionyl chloride and toluene were removed under reduced pressure. The dark oil obtained was decolorized using activated carbon and was used as is without further purification.

[0094] N-methyl-2-hexyl-7-(methylphosphonate)carbazole (33): In a 25 mL flask were added compound **32** (2.10 g, 6.80 mmol) and triethylphosphite (10 mL). The resulting solution was refluxed for 24 h under argon atmosphere. Excess triethylphosphite was removed under reduced pressure. The crude product was purified by column chromatography (silica gel, 30 % acetone in hexanes as eluent) to provide 2.42 g of the title product as an orange solid. M.P.: 61-62°C (Yield: 86 %). ¹H NMR (400MHz, CDCl₃, ppm): 7.97 (m, 2H); 7.35 (m, 1H); 7.19 (s, 1H); 7.13 (dt, 1H, *J* = 7.9 et 1.6 Hz); 7.08 (dd, 1H, *J* = 7.9 et 1.4 Hz); 4.00 (m, 4H); 3.81 (s, 3H); 3.36 (d, 2H, *J* = 21.4 Hz); 2.82 (t, 2H, *J* = 7.7 Hz); 1.74 (m, 2H); 1.37 (m, 6H); 1.24 (t, 6H, *J* = 7.1 Hz); 0.92 (t, 3H, *J* = 7.0 Hz). ¹³C NMR (100 MHz, CDCl₃, ppm): 141.84; 141.59; 141.56; 141.35; 141.34; 129.58; 129.50; 122.06; 122.03; 120.95; 120.89; 120.71; 120.69; 120.12; 120.09; 120.08; 109.85; 109.77; 108.25; 62.43; 62.37; 37.03; 35.34; 33.97; 32.36; 32.04; 29.35; 29.24;

22.88; 16.67; 16.61; 14.37.

[0095] *N*-methyl-2-hexyl-7-(formyl)carbazole (34): To a solution of compound 31 (2.00 g, 6.89 mmol) in anhydrous dichloromethane (75 mL) at 0°C were added pyridinium chlorochromate (PCC) (2.97 g, 13.9 mmol, Aldrich Co.),
 5 molecular sieves 4Å (1.14 g) and silica gel (1.14 g). The resulting solution was stirred under argon atmosphere for 2 h at room temperature and then filtered onto silica gel (dichloromethane as eluent) to provide the title product as a bright yellow solid. M.P.: 55-56°C (Yield: 85 %). ¹H NMR (400MHz, CDCl₃, ppm): 10.14 (s, 1H); 8.15 (d, 1H, *J* = 8.0 Hz); 8.03 (d, 1H, *J* = 8.0 Hz); 7.93 (s, 1H); 7.72 (dd, 1H, *J* = 8.0 et 1.4 Hz); 7.24 (s, 1H); 7.13 (dd, 1H, *J* = 8.0 et 1.3 Hz); 3.90 (s, 3H); 2.83 (t, 2H, *J* = 7.7 Hz); 1.73 (m, 2H); 1.34 (m, 6H); 0.90 (t, 3H, *J* = 7.0 Hz). ¹³C NMR (100 MHz, CDCl₃, ppm): 192.90; 143.74; 143.43; 140.93; 133.58; 128.43; 121.62; 121.30; 121.00; 120.29; 120.00; 109.50; 108.63; 37.11; 32.18; 31.99; 29.43; 29.31; 22.85; 14.35.

15 [0096] 5,5'-diformyl-2,2'-bithiophene (35): To a solution of 5,5'-dibromo-2,2'-bithiophene (2.00 g, 6.17 mmol, Aldrich Co.) in anhydrous THF (30 mL) was added dropwise *n*-butyllithium (5.43 mL, 13.6 mmol, 2.5 M in hexanes, Aldrich Co.) at -78°C under argon. The mixture was stirred 30 min. at -78°C, warmed to room temperature and stirred for an additional 90 minutes. Anhydrous
 20 dimethylformamide (1.43 mL, 18.5 mmol, Aldrich Co.) was added dropwise and the solution was stirred at room temperature for another 2 h. An aqueous HCl solution (1 M, 10 mL) was slowly added followed by the addition of acetone (50 mL). The resulting mixture was poured into 150 mL of hexanes at 0°C and the brown precipitate was filtered, washed with hexanes and dried under vacuum for 24 h to
 25 provide 1.05 g of the title product as a orange-brown solid. M.P.: 213-214°C (Yield: 76 %). ¹H NMR (400 MHz, DMSO-*d*₆, ppm): 9.89 (s, 2H); 8.00 (d, 2H, *J* = 4.0 Hz); 7.73 (d, 2H, *J* = 4.0 Hz). ¹³C NMR (100 MHz, DMSO-*d*₆, ppm): 185.00; 144.14; 144.03; 139.60; 128.57.

[0097] The following examples provide preferred embodiments of oligomers and polymers as contemplated by the present invention. Examples 1-6 are drawn to oligomers, whereas examples 7-14 are drawn to polymers.

EXAMPLE 1

- 5 [0098] **N-hexyl-2,7-bis(vinylene)phenylene)carbazole (36) (PCP):** To a solution of compound 18 (500 mg, 0.91 mmol) and benzaldehyde (240 mg, 2.27 mmol, Aldrich Co.) in anhydrous THF (20 mL) was slowly added potassium *tert*-butoxide (470 mg, 4.19 mmol, Aldrich Co.). The mixture was stirred at room temperature for 16 h and then poured into 300 mL of methanol. The yellow
- 10 precipitate was filtered and washed thoroughly with methanol to provide 394 mg of the title product as a yellow solid. M.P.: 198-200°C (Yield: 95 %). ¹H NMR (400 MHz, CDCl₃, ppm): 8.02 (d, 2H, J = 8.0 Hz); 7.61 (d, 4H, J = 7.3 Hz); 7.42 (m, 8H); 7.28 (m, 6H); 4.32 (t, 2H, J = 7.2 Hz); 1.94 (m, 2H); 1.41 (m, 6H); 0.94 (t, 3H, J = 7.0 Hz). ¹³C NMR (100 MHz, CDCl₃, ppm): 141.72; 137.84; 135.36; 130.07;
- 15 128.96; 128.29; 127.70; 126.73; 122.77; 120.69; 118.05; 107.12; 43.22; 31.87; 29.23; 27.25; 22.85; 14.35.

EXAMPLE 2

- [0099] **N-hexyl-2,7-bis(vinylene-(N-hexyl-2-carbazole))carbazole (37) (CCC):** To a solution of compound 28 (500 mg, 1.25 mmol) and compound 13 (179
- 20 mg, 0.59 mmol) in anhydrous THF (25 mL) was slowly added potassium *tert*-butoxide (560 mg, 5.00 mmol, Aldrich Co.). The mixture was stirred at room temperature for 16 h and then poured into 100 mL of water. The aqueous layer was washed three times with chloroform and the combined organic layer was washed three times with water. The organic layer was dried over magnesium
- 25 sulfate and concentrated under reduced pressure. The residue was purified by column chromatography (chloroform as eluent) followed by precipitation in cold

methanol to provide 400 mg of the title product as a green solid. M.P.: 228-230°C (Yield: 82 %). ¹H NMR (400 MHz, CDCl₃, ppm): 8.08 (m, 6H); 7.54 (m, 8H); 7.46 (m, 8H); 7.23 (m, 2H); 4.35 (m, 6H); 1.93 (m, 6H); 1.40 (m, 18H); 0.90 (m, 9H). ¹³C NMR (100 MHz, CDCl₃, ppm): 141.78; 141.28; 141.14; 135.62; 135.60; 129.47; 129.41; 125.80; 123.02; 122.70; 122.68; 120.74; 120.64; 120.49; 119.13; 118.06; 117.81; 108.90; 106.97; 106.96; 43.28 (2C); 31.90; 31.86; 29.26; 29.22; 27.27; 27.24; 22.86; 22.82; 14.35; 14.30.

EXAMPLE 3

[00100] 5,5'-bis(vinylene-(N-hexyl-2-carbazole))-2,2'-bithiophene (38)

(CTTC): To a solution of compound 28 (500 mg, 1.25 mmol) and 35 (133 mg, 0.58 mmol) in anhydrous THF (25 mL) was slowly added potassium *tert*-butoxide (560 mg, 5.00 mmol, Aldrich Co.). The mixture was stirred at room temperature for 16 h and then poured into 100 mL of water. The aqueous layer was washed three times with chloroform and the combined organic layer was washed three times with water. The organic layer was dried over magnesium sulfate and concentrated under reduced pressure. The residue was purified by column chromatography (chloroform as eluent) followed by precipitation in cold methanol to provide 217 mg of the title product as an orange solid. M.P.: 207-209°C (Yield: 49 %). ¹H NMR (400 MHz, CDCl₃, ppm): 8.07 (t, 4H, *J* = 6.5 Hz); 7.43 (m, 8H); 7.27 (m, 4H); 7.13 (m, 4H); 7.03 (d, 2H, *J* = 3.8 Hz); 4.32 (t, 4H, *J* = 7.4 Hz); 1.90 (m, 4H); 1.38 (m, 12H); 0.89 (t, 6H, *J* = 7.0 Hz). ¹³C NMR (100 MHz, CDCl₃, ppm): 142.55; 141.31; 141.05; 136.21; 134.78; 129.92; 127.26; 125.91; 124.33; 122.94; 122.88; 121.18; 120.78; 120.51; 119.17; 117.54; 108.91; 106.96; 43.29; 31.83; 29.19; 27.22; 22.80; 14.27.

EXAMPLE 4

[00101] ***N*-(2-ethylhexyl)-2,7-bis(vinylene-4-(1,1'-biphenylene))carbazole (BPCBP) (39):** In a 25 mL flask, compound 20 (200 mg, 0.61 mmol), 4-bromo-1,1'-biphenyl (354 mg, 1.52 mmol, Aldrich Co.), palladium (II) acetate (5.50 mg, 0.02 mmol, Aldrich Co.), tri-*o*-tolylphosphine (37.0 mg, 0.12 mmol, Aldrich Co.) and degassed anhydrous DMF (4 mL) were mixed under argon. The solution was heated at 80°C followed by the addition of triethylamine (0.21 mL, 1.53 mmol, Aldrich Co.). The resulting solution was stirred at 110°C under argon for 24 h. The mixture was cooled at room temperature and poured into water (150 mL). The aqueous layer was washed three times with chloroform (100 mL) and the combined organic fractions were dried with magnesium sulfate. The solvent was removed under reduced pressure and the crude green solid was completely dissolved in 150 mL of hot benzene. This solution was poured into methanol (300 mL) under vigorous stirring and the green precipitate was collected by filtration.

15 The latter step was repeated twice to provide 263 mg of the title product as a green solid. M.P. >260°C (Yield: 68 %). ¹H NMR (400 MHz, CDCl₃, ppm): 8.04 (d, 2H, *J* = 8.6 Hz); 7.65 (m, 12H); 7.47 (m, 8H); 7.36 (m, 4H); 7.26 (m, 2H); 4.24 (m, 2H); 2.16 (m, 1H); 1.40 (m, 8H); 0.98 (t, 3H, *J* = 7.3 Hz); 0.92 (t, 3H, *J* = 7.2 Hz).

20 ¹³C NMR (100 MHz, CDCl₃, ppm): 142.25; 140.91; 140.36; 136.85; 135.32; 130.11; 129.02; 127.77; 127.59; 127.52; 127.12; 127.09; 122.74; 120.62; 118.03; 107.41; 47.59; 39.61; 31.17; 29.01; 24.73; 23.31; 14.36; 11.24.

EXAMPLE 5

[00102] ***N*-hexyl-2,7-bis(cyanovinylphenylene)carbazole (PCP-CN) (40):** In a 25 mL flask, compound 13 (500 mg, 1.63 mmol), benzyl cyanide (457 mg, 3.90 mmol) and methanol (16 mL) were mixed under argon. A catalytic amount of potassium *tert*-butoxide was added and the solution was stirred at room temperature under argon for 24 h. The green-yellow precipitate formed during the

reaction was filtered, rinsed with methanol and dried under reduced pressure to provide 722 mg of the title product as a bright green-yellow powder. M.P.: 126-128°C (Yield: 88 %). ¹H NMR (400 MHz, CDCl₃, ppm): 8.09 (m, 3H); 8.07 (s, 1H); 7.72 (m, 2H); 7.70 (m, 2H); 7.66 (s, 2H); 7.62 (m, 2H); 7.45 (m, 4H); 7.39 (m, 2H); 4.33 (t, 2H, J = 7.3 Hz); 1.94 (m, 2H); 1.44 (m, 2H); 1.33 (m, 4H); 0.87 (t, 3H, J = 7.1 Hz). ¹³C NMR (100 MHz, CDCl₃, ppm): 143.07; 141.72; 134.89; 132.05; 129.28; 129.25; 126.14; 124.30; 121.76; 121.27; 118.83; 110.70; 109.41; 43.65; 31.77; 29.22; 27.22; 22.78; 14.26.

EXAMPLE 6

- 10 [00103] **1,4-bis(vinylene-(N-hexyl-7-hexyl-2-carbazole))phenylene (H-CPC-H) (41):** To a solution of compound 34 (1.03 g, 3.51 mmol) and 1,4-bis(methylphosphonate)benzene (0.53 g, 1.41 mmol) in anhydrous THF (15 mL) was added sodium *tert*-butoxide (0.54 g, 5.63 mmol). The resulting mixture was stirred under an argon atmosphere for 24 h at room temperature, which was
- 15 followed by the addition of methanol (10 mL). The green-yellow precipitate so-obtained was collected by filtration, rinsed thoroughly with acetone and dried under reduced pressure for 24 h to provide 855 mg of the title product as a green-yellow solid (Yield = 79 %). M.P.: 280°C (determined by DSC analysis at a scan rate of 10°C/minute). H-CPC-H was not soluble enough for NMR analysis.

20

EXAMPLE 7

- [00104] **Poly(N-(2-ethylhexyl)-2,7-carbazolenevinylene) (PCV) by McMurry reaction²³:** In a 100 mL flask, zinc powder (1.17 g, 17.9 mmol, Aldrich Co.) and anhydrous THF (15 mL) were mixed under argon. The resulting suspension was cooled to 0°C in a ice/water bath and titanium (IV) chloride (1.70
- 25 g, 8.94 mmol, Aldrich Co.) was slowly added. The mixture was stirred at reflux for 1h and then a solution of compound 12 (0.50 g, 1.49 mmol) in anhydrous THF (5

5 mL) was slowly added. The resulting solution was stirred for 24 h at reflux and then cooled to room temperature. An aqueous Na_2CO_3 solution (10 %) was added and the resulting solution was stirred for 10 min. The precipitate was filtered, rinsed thoroughly with water, and then with methanol and washed in a soxhlet apparatus using acetone for 48 h to provide the title product as a yellow powder.

EXAMPLE 8

[00105] Poly(N-(2-ethylhexyl)-2,7-carbazole-*alt*-2,5-dioctyloxy-1,4-phenylenevinylene) (PCVP) by Wittig reaction: In a 25 mL flask, compound 19 (1.00 g, 1.11 mmol), 2,5-dioctyloxy-1,4-diformylbenzene (434 mg, 1.11 mmol), anhydrous ethanol (4 mL) and anhydrous chloroform (6 mL) were mixed under argon and the resulting solution was cooled to 0°C. Sodium ethoxide (378 mg, 5.55 mmol) was slowly added and the solution was warmed to room temperature and stirred under argon for 24 h. The solution was poured into 200 mL of methanol and the precipitate was filtered, rinsed thoroughly with methanol and washed in a soxhlet apparatus using acetone for 48 h to provide the title product as an orange powder.

EXAMPLE 9

[00106] Poly(N-(2-ethylhexyl)-2,7-carbazole-*alt*-2,5-dioctyloxy-1,4-phenylenevinylene) (PCVP) by Wittig-Horner reaction: In a 25 mL flask, compound 17 (571 mg, 0.99 mmol), 2,5-dioctyloxy-1,4-diformylbenzene (385 mg, 0.99 mmol) and anhydrous THF (10 mL) were mixed under argon. Potassium *tert*-butoxide (443 mg, 3.96 mmol) was slowly added and the solution was stirred at room temperature under argon for 24 h. The resulting solution was poured into 200 mL of methanol and the precipitate was filtered, rinsed thoroughly with methanol and washed in a soxhlet apparatus using acetone for 48 h to provide the title product as an orange solid having good film forming properties.

EXAMPLE 10

[00107] Poly(N-(2-ethylhexyl)-2,7-carbazolenecyanovinylene-*alt*-2,5-dioctyloxy-1,4-phenylenevinylene) (PCCVP) by Knoevenagel reaction: In a 25 mL flask, compound 14 (250 mg, 0.70 mmol), 2,5-dioctyloxy-1,4-diformylbenzene (273 mg, 0.70 mmol), anhydrous THF (4 mL) and anhydrous *tert*-butyl alcohol were mixed under argon. A catalytic amount of potassium *tert*-butoxide was added and the solution was stirred at room temperature under argon for 24 h. The resulting solution was poured into 200 mL of methanol and the precipitate was filtered, rinsed thoroughly with water, followed by rinsing with methanol and washing in a soxhlet apparatus using acetone for 48 h to provide the title product as a red solid having good film forming properties.

EXAMPLE 11

[00108] Poly(N-(2-ethylhexyl)-2,7-carbazolenevinylene-co-2,5-bis(diphenylamine)-1,4-phenylenevinylene-co-((4-(2-ethylhexyloxy)-phenyl)-bis-(4'-phenylene)amine) (PCVDPATA) by Wittig-Horner reaction: In a 25 mL flask, compound 17 (343 mg, 0.60 mmol), 2,5-bis(diphenylamino)terephthaldicarboxaldehyde (139 mg, 0.30 mmol), [4-(2-ethylhexyloxy)-phenyl]-bis-(4'-formylphenyl) (127 mg, 0.30 mmol) and anhydrous THF (12 mL) were mixed under argon. Potassium *tert*-butoxide (265 mg, 2.37 mmol) was slowly added and the solution was stirred at room temperature under argon for 24 h. The resulting solution was poured into 200 mL of methanol and the orange precipitate was filtered, rinsed thoroughly with methanol and washed in a soxhlet apparatus using acetone for 48 h to provide the title product as an orange solid having good film forming properties.

EXAMPLE 12

[00109] Poly(N-(2-ethylhexyl-2,7-carbazolenecyanovinylene-co-2,5-bis(diphenylamine)-1,4-phenylenecyanovinylene-co-2,5-dioctyloxy-1,4-phenylenecyanovinylene) (PCVDPAP) by Knoevenagel reaction: In a 25 mL flask, compound 14 (250 mg, 0.70 mmol), 2,5-bis(diphenylamino)terephthalaldehyde (164 mg, 0.35 mmol), 2,5-dioctyloxy-1,4-diformylbenzene (137 mg, 0.35 mmol), anhydrous THF (5 mL) and anhydrous *tert*-butyl alcohol (5 mL) were mixed under argon. A catalytic amount of potassium *tert*-butoxide was added and the solution was stirred at room temperature under argon for 24 h. The resulting solution was poured into 200 mL of methanol and the precipitate was filtered, rinsed thoroughly with water followed by methanol and washed in a soxhlet apparatus using acetone for 48 h to provide the title product as a red solid having good film forming properties.

EXAMPLE 13

[00110] Poly(N-(2-ethylhexyl-2,7-carbazolenevinylene-*alt*-5,6'-(2,2'-bis(2''-ethylhexyloxy)-1,1'-binaphthyl) (PCVBN) by Heck reaction: In a 25 mL flask, compound 20 (200 mg, 0.61 mmol), 6,6'-dibromo-2,2'-bis(2''-ethylhexyloxy)-1,1'-binaphthyl (406 mg, 0.61 mmol, Aldrich Co.), palladium (II) acetate (14.0 mg, 0.06 mmol, Aldrich Co.), tetrabutylammonium chloride (202 mg, 0.61 mmol, Aldrich Co.), freshly dried lithium chloride (26.0 mg, 0.61 mmol), anhydrous potassium carbonate (168 mg, 1.22 mmol) and degassed anhydrous DMF (18 mL) were mixed under argon. The solution was heated at 120°C and stirred under argon for 72 h. The resulting solution was poured into 200 mL of cold methanol and the precipitate was filtered, rinsed thoroughly with water followed by methanol and washed in a soxhlet apparatus using acetone for 48 h to provide the title product as a yellow solid.

EXAMPLE 14

[00111] Poly[(N-(4-octyloxyphenyl))-2,7-carbazolenevinylene-*alt*-(3-hexyl-2,5-thiophenevinylene)] (PPCVT) by Horner-Emmons reaction: In a 25 mL flask, compound 22 (412 mg, 0.96 mmol), 3-hexyl-2,5-bis(methylphosphonate)thiophene (452 mg, 0.96 mmol) and anhydrous THF (11 mL) were mixed under argon. Potassium *tert*-butoxide (471 mg, 3.85 mmol) was slowly added and the solution was stirred at room temperature under argon for 24 h. The resulting solution was poured into 200 mL of methanol and the orange precipitate was filtered, rinsed thoroughly with methanol and washed in a soxhlet apparatus using acetone for 48 h to provide the title product as a red solid having good film forming properties.

[00112] Although the present invention has been described hereinabove by way of preferred embodiments thereof, it can be modified, without departing from the spirit and nature of the subject invention as defined in the appended claims.


REFERENCES

1. *Handbook of Conducting Polymers*, 2nd ed.; Skotheim, T.A.; Elsenbaumer, R.L.; Reynolds, J.R.; Eds. Marcel Dekker, New York, 1998.
2. Leclerc, M.; Faïd, K. *Adv. Mater.* **1997**, *9*, 1087; Leclerc, M. *Adv. Mater.* **1999**, *11*, 1491; McQuade, D.T.; Pullen, A.E.; Swager, T.M. *Chem. Rev.* **2000**, *100*, 2537; Ho, H.A.; Boissinot, M.; Bergeron, M.G.; Corbeil, G.; Doré, K.; Boudreau, D.; Leclerc, M. *Angew. Chem. Int. Ed.* **2002**, *41*, 1548.
3. Burroughes, J. H.; Bradley, D. D. C.; Brown, A. R.; Marks, R. N.; MacKay, K.; Friend, R. H.; Burns, P. L.; Holmes, A. B. *Nature* **1990**, *347*, 539.
4. Mitschke, U.; Bauerle, P. *J. Mater. Chem.* **2000**, *10*, 1471.
5. Kraft, A.; Grimsdale, A.C.; Holmes, A.B. *Angew. Chem. Int. Ed.* **1998**, *37*, 402.
6. Bernius, M.T.; Inbasekaran, M.; O'Brien, J.; Wu, W. *Adv. Mater.* **2000**, *12*, 1737; Leclerc, M. *J. Polym. Sci., Polym. Chem.* **2001**, *39*, 2867; Neher, D.
- 15 *Macromol. Rapid Commun.* **2001**, *22*, 1365.
7. Brabec, C. J.; Sariciftci, N. S.; Hummelen, J. C. *Adv. Funct. Mater.* **2002**, *12*, 192; Sariciftci, N. S.; Braun, D.; Zhang, C.; Srdanov, V. I.; Heeger, A. J.; Stucky, G.; Wudl, F. *Appl. Phys. Lett.* **1993**, *62*, 585.
8. Morin, J.-F.; Leclerc, M. *Macromolecules* **2001**, *34*, 4680.
- 20 9. Zotti, G.; Schiavon, G.; Zecchin, S.; Morin, J.-F.; Leclerc, M. *Macromolecules* **2002**, *35*, 2122.
10. Morin, J.-F.; Leclerc, M.; *Macromolecules* **2002**, *35*, 8413.
11. Morin, J.-F.; Beaupré, S.; Leclerc, M.; Lévesque, I.; D'Iorio, M. *Appl. Phys. Lett.* **2002**, *80*, 341.
- 25 12. Drolet, N.; Beaupré, S.; Morin, J.-F.; Tao, Y.; Leclerc, M. *J. Opt. A: Pure Appl. Opt.*, **2002**, *4*, S252.

13. DiCesare, N.; Belletête, M.; Leclerc, M.; Durocher, G. *Chem. Phys. Lett.* **1998**, *291*, 487; Donat-Bouillud, A. Ph. D. Thesis, 1998, Université de Montréal.
14. Pavlopoulos, T. G.; Boyer, J. H.; Shah, M.; Thangaraj, K.; Soong, M.L. *Appl. Opt.* **1990**, *29*, 3885.
- 5 15. Shi, J.; Zheng, S. *Macromolecules* **2001**, *34* (19), 6571.
16. Kim, S. W.; Shim, S. C.; Jung, B.-J.; Shim, H.-K. *Polymer* **2002**, *43*, 4297.
17. Sarker, A. M.; Ding, L.; Lahti, P. M.; Karasz, F. E. *Macromolecules* **2002**, *35*, 223.
18. Zheng, L.; Urian, R. C.; Liu, Y.; Jen, A. K.-Y.; Pu, L. *Chem. Mater.* **2000**,
10 12, 13.
19. Chen, Y.; Huang, Y. Y.; Wu, T. Y. *J. Polym. Sci. Part A* **2002**, *40*, 2927.
20. Chaudhary, S. K.; Hernandez, O. *Tet. Lett.* **1979**, *2*, 95.
21. Liu, B.; Yu, W.-L.; Pei, J.; Liu, S.-Y.; Lai, Y.-H.; Huang, W. *Macromolecules* **2001**, *34* (23), 7932.
- 15 22. Gómez, R.; Segura, J. L.; Martín, N. *J. Org. Chem.* **2000**, *65*, 7501.
23. Goldoni, F.; Janssen, A. J.; Meljer, E. W. *J. Polym. Sci. Part A* **1999**, *37*, 4629.

WHAT IS CLAIMED IS:

1. A compound of Formula I:


**Formula I**


- 5 wherein:

R^1 is selected from the group consisting of H, alkyl, and aryl;

R^2 and R^3 are independently selected from the group consisting of H, alkyl, formyl, hydroxymethyl, trityloxymethyl, acetonitrile, chloromethyl, methylphosphonate, methyltriphenylphosphonium and vinyl.


- 10 2. A compound as defined in claim 1, selected from the group consisting of:





wherein R^1 is as previously defined.


3. A compound as defined in claim 1, selected from the group consisting of:



5

wherein R^1 is as previously defined.

4. A compound as defined in claims 2 and 3 having the formula:




wherein R¹ is alkyl.

5. A compound as defined in claim 4, wherein R¹ is hexyl or 2-ethylhexyl.

6. A compound as defined in claim 4, wherein R¹ is aryl.

7. A compound as defined in claim 4, wherein R¹ is 4-octyloxyphenyl.


8. A compound as defined in claims 2 and 3 having the formula:



wherein R¹ is alkyl.

9. A compound as defined in claim 8, wherein R¹ is hexyl or 2-ethylhexyl.


10. A compound as defined in claims 2 and 3 having the formula:



wherein R¹ is alkyl.

11. A compound as defined in claim 10, wherein R¹ is 2-ethylhexyl.


12. A compound as defined in claims 2 and 3 having the formula:



wherein R^1 is alkyl.

13. A compound as defined in claim 12, wherein R^1 is 2-ethylhexyl.


14. A compound as defined in claims 2 and 3 having the formula:



wherein R^1 is alkyl.

15. A compound as defined in claim 14, wherein R^1 is 2-ethylhexyl.


16. A compound as defined in claim 2 having the formula:



wherein R^1 is alkyl.

17. A compound as defined in claim 16, wherein R^1 is hexyl or 2-ethylhexyl.

18. A compound as defined in claim 2 having the formula:




wherein R^1 is H or alkyl.

19. A compound as defined in claim 18, wherein R^1 is hexyl or 2-ethylhexyl.

20. A compound as defined in claim 18, wherein R^1 is aryl.

5 21. A compound as defined in claim 20, wherein R^1 is 4-octyloxyphenyl.


22. A compound as defined in claim 2 having the formula:



wherein R^1 is alkyl.

10 23. A compound as defined in claim 22, wherein R^1 is hexyl.


24. A compound as defined in claim 2 having the formula:



wherein R^1 is H or alkyl.

25. A compound as defined in claim 24, wherein R^1 is hexyl.


15 26. A compound as defined in claim 2 having the formula:



wherein R^1 is alkyl.

27. A compound as defined in claim 26, wherein R^1 is hexyl.


28. A compound as defined in claim 2 having the formula:



wherein R^1 is alkyl.

29. A compound as defined in claim 28, wherein R^1 is hexyl.


- 5 30. A compound as defined in claim 2 having the formula:



wherein R^1 is alkyl.

31. A compound as defined in claim 30, wherein R^1 is hexyl.


32. A compound as defined in claim 2 having the formula:



10 wherein R^1 is alkyl.

33. A compound as defined in claim 32, wherein R^1 is hexyl.


34. A compound as defined in claim 2 having the formula:



15 wherein R^1 is H or alkyl.

35. A compound as defined in claim 34, wherein R^1 is methyl.


36. A compound as defined in claim 2 having the formula:



wherein R¹ is alkyl.

37. A compound as defined in claim 36, wherein R¹ is methyl.


- 5 38. A compound as defined in claim 2 having the formula:



wherein R¹ is alkyl.

39. A compound as defined in claim 38, wherein R¹ is methyl.


40. A compound as defined in claim 2 having the formula:



10 wherein R¹ is alkyl.

41. A compound as defined in claim 40, wherein R¹ is methyl.

42. A compound as defined in claim 2 having the formula:




15 wherein R¹ is alkyl.

43. A compound as defined in claim 42, wherein R¹ is methyl.

44. An oligomer comprising the reaction product of a first compound of Formula I and at least a second compound, said second compound being either a compound of Formula 1; benzaldehyde; 5,5'-diformyl-2,2'-bithiophene, 4-bromo-1,1'-biphenyl; benzyl cyanide; or 1,4-bis(methylphosphonate)benzene.

45. An oligomer as defined in claim 44 having the formula:




wherein R^1 is selected from the group consisting of H, alkyl, and aryl.

46. An oligomer as defined in claim 45, wherein R^1 is alkyl.

47. An oligomer as defined in claim 46, wherein R^1 is hexyl or 2-ethylhexyl.

48. An oligomer as defined in claim 47, wherein R^1 is hexyl.

49. An oligomer as defined in claim 45 wherein the first compound of Formula I is of the formula:



wherein R^1 is selected from the group consisting of H, alkyl, and aryl.


50. An oligomer as defined in claim 49, wherein R^1 is alkyl.

51. An oligomer as defined in claim 50, wherein R^1 is hexyl or 2-ethylhexyl.

52. An oligomer as defined in claim 51, wherein R^1 is hexyl.

53. An oligomer as defined in any one of claims 45 to 52, wherein the second compound is benzaldehyde.

54. An oligomer as defined in claim 44 having the formula:




5 wherein R^1 is selected from the group consisting of H, alkyl, and aryl.

55. An oligomer as defined in claim 54, wherein R^1 is alkyl.

56. An oligomer as defined in claim 55, wherein R^1 is hexyl or 2-ethylhexyl.

57. An oligomer as defined in claim 56, wherein R^1 is hexyl.

10 58. An oligomer as defined in claim 54 wherein the first compound of Formula I is of the formula:



wherein R^1 is selected from the group consisting of H, alkyl, and aryl.

59. An oligomer as defined in claim 58, wherein R^1 is alkyl.


15 60. An oligomer as defined in claim 59, wherein R^1 is hexyl or 2-ethylhexyl.

61. An oligomer as defined in claim 59, wherein R^1 is hexyl.

62. An oligomer as defined in claim 58, wherein R^1 is aryl.

20 63. An oligomer as defined in claim 62, wherein R^1 is 4-octyloxyphenyl.

64. An oligomer as defined in claim 54 wherein the second compound of Formula I is of the formula:




wherein R¹ is selected from the group consisting of H, alkyl, and aryl.

65. An oligomer as defined in claim 64, wherein R¹ is alkyl.

66. An oligomer as defined in claim 65, wherein R¹ is hexyl.

67. An oligomer as defined in claim 44 having the formula:




wherein R¹ is selected from the group consisting of H, alkyl, and aryl.

68. An oligomer as defined in claim 67, wherein R¹ is alkyl.

69. An oligomer as defined in claim 68, wherein R¹ is hexyl.

70. An oligomer as defined in claim 67 wherein the first compound of Formula I is of the formula:




wherein R¹ is selected from the group consisting of H, alkyl, and aryl.

71. An oligomer as defined in claim 70, wherein R¹ is alkyl.

72. An oligomer as defined in claim 71, wherein R¹ is hexyl.

73. An oligomer as defined in any one of claims 67 to 72, wherein the second compound is 5,5'-diformyl-2-2'bithiophene.

74. An oligomer as defined in claim 44 having the formula:




5 wherein R¹ is selected from the group consisting of H, alkyl, and aryl.

75. An oligomer as defined in claim 74, wherein R¹ is alkyl.

76. An oligomer as defined in claim 75, wherein R¹ is 2-ethylhexyl.

10 77. An oligomer as defined in claim 74 wherein the first compound of Formula I is of the formula:




wherein R¹ is selected from the group consisting of H, alkyl, and aryl.

78. An oligomer as defined in claim 77, wherein R¹ is alkyl.

15 79. An oligomer as defined in claim 78, wherein R¹ is 2-ethylhexyl.

80. An oligomer as defined in any one of claims 74 to 79, wherein the second compound is 4-bromo-1,1'biphenyl.

81. An oligomer as defined in claim 44 having the formula:



wherein R¹ is selected from the group consisting of H, alkyl, and aryl.


82. An oligomer as defined in claim 81, wherein R¹ is alkyl.

- 5 83. An oligomer as defined in claim 82, wherein R¹ is hexyl or 2-ethylhexyl.

84. An oligomer as defined in claim 81, wherein R¹ is aryl.

85. An oligomer as defined in claim 84, wherein R¹ is 4-octyloxyphenyl.

- 10 86. An oligomer as defined in claim 81 wherein the first compound of Formula I is of the formula:



wherein R¹ is selected from the group consisting of H, alkyl, and aryl.

87. An oligomer as defined in claim 86, wherein R¹ is alkyl.

- 15 88. An oligomer as defined in claim 87, wherein R¹ is hexyl or 2-ethylhexyl.


89. An oligomer as defined in claim 88, wherein R¹ is hexyl.

90. An oligomer as defined in claim 86, wherein R¹ is aryl.

91. An oligomer as defined in claim 90, wherein R^1 is 4-octyloxyphenyl.

92. An oligomer as defined in any one of claims 81 to 91, wherein the second compound is benzyl cyanide.

5 93. An oligomer as defined in claim 44 having the formula:




wherein R^1 is selected from the group consisting of H, alkyl, and aryl.

94. An oligomer as defined in claim 93, wherein R^1 is alkyl.

95. An oligomer as defined in claim 94, wherein R^1 is methyl.

10 96. An oligomer as defined in claim 93, wherein the first compound of Formula I is of the formula:



wherein R^1 is selected from the group consisting of H, alkyl, and aryl.

97. An oligomer as defined in claim 96, wherein R^1 is alkyl.


15 98. An oligomer as defined in claim 97, wherein R^1 is methyl.

99. An oligomer as defined in any one of claims 93 to 98, wherein the second compound is 1,4-(bis)methylphosphonate)benzene.

100. A polymer comprising the reaction product of a compound of Formula I and optionally at least one compound selected from the group consisting of

- 2,5-dioctyloxy-1,4-diformylbenzene; 2,5-bis(diphenylamino)terephthalaldehyde; {4-(2-ethylhexyloxy)-phenyl}-bis-(4'-formylphenyl); 6,6'-dibromo-2,2'-bis(2"-ethylhexyloxy)-1,1'-binaphthyl; and 3-hexyl-2,5-bis(methylphosphonate)thiophene.

101. A polymer as defined in claim 100, comprising monomeric groups of the formula:




- 102 wherein R¹ is selected from the group consisting of H, alkyl, and aryl.

102. A polymer as defined in claim 101, wherein R¹ is alkyl.

103. A polymer as defined in claim 102, wherein R¹ is hexyl or 2-ethylhexyl.


104. A polymer as defined in claim 103, wherein R¹ is 2-ethylhexyl.

105. A polymer as defined in claim 104 having the formula:



wherein "n" is an integer ranging from 5 to 100.

106. A polymer as defined in claim 100, comprising monomeric groups of the formula:




wherein R¹ is selected from the group consisting of H, alkyl, and aryl.

107. A polymer as defined in claim 106, wherein R¹ is alkyl.

108. A polymer as defined in claim 107, wherein R¹ is hexyl or 2-ethylhexyl.


109. A polymer as defined in claim 108, wherein R¹ is 2-ethylhexyl.

110. A polymer as defined in claim 109 having the formula:



wherein "n" is an integer ranging from 5 to 100.

111. A polymer as defined in claim 100, comprising monomeric groups of the formula:




wherein R¹ is selected from the group consisting of H, alkyl, and aryl.

112. A polymer as defined in claim 111, wherein R¹ is alkyl.

113. A polymer as defined in claim 112, wherein R¹ is hexyl or 2-ethylhexyl.

114. A polymer as defined in claim 113, wherein R¹ is 2-ethylhexyl.


115. A polymer as defined in claim 114 having the formula:



5

wherein "n" is an integer ranging from 5 to 100.

116. A polymer as defined in claim 100, comprising monomeric groups of the formula:



10 wherein R¹ is selected from the group consisting of H, alkyl, and aryl.


117. A polymer as defined in claim 116, wherein R¹ is alkyl.

118. A polymer as defined in claim 117, wherein R¹ is hexyl or 2-ethylhexyl.

119. A polymer as defined in claim 118, wherein R¹ is 2-ethylhexyl.


15

120. A polymer as defined in claim 119 having the formula:



wherein "n", "m", and "o" are integers ranging from 5 to 100.

121. A polymer as defined in claim 100, comprising monomeric groups of the formula:



wherein R¹ is selected from the group consisting of H, alkyl, and aryl.


122. A polymer as defined in claim 121, wherein R¹ is alkyl.

123. A polymer as defined in claim 122, wherein R¹ is hexyl or 2-

ethylhexyl.


124. A polymer as defined in claim 123, wherein R¹ is 2-ethylhexyl.

125. A polymer as defined in claim 124 having the formula:



wherein "n", "m", and "o" are integers ranging from 5 to 100.

126. A polymer as defined in claim 100, comprising monomeric groups of the formula:




wherein R¹ is selected from the group consisting of H, alkyl, and aryl.

127. A polymer as defined in claim 126, wherein R¹ is alkyl.

128. A polymer as defined in claim 127, wherein R¹ is hexyl or 2-ethylhexyl.


129. A polymer as defined in claim 128, wherein R¹ is 2-ethylhexyl.

130. A polymer as defined in claim 129 having the formula:



wherein "n" is an integer ranging from 5 to 100.

131. A polymer as defined in claim 100, comprising monomeric groups of the formula:




wherein R¹ is selected from the group consisting of H, alkyl, and aryl.

5 132. A polymer as defined in claim 131, wherein R¹ is aryl.

133. A polymer as defined in claim 132, wherein R¹ is 4-octyloxyphenyl.

134. A polymer as defined in claim 133 having the formula:



10 wherein "n" is an integer ranging from 5 to 100.

135. A composition comprising the oligomer and/or polymer of claims 44-134.

136. An electronic device comprising a film or coating comprising the oligomer and/or polymer of claims 44-134.

15 137. The electronic device of claim 136, configured as a light-emitting diode.

138. The electronic device of claim 136, configured as a field-effect transistor.

139. The electronic device of claim 136, configured as a solar cell.




Figure 1




Figure 1 (continued)




Figure 2




Figure 3




Figure 4

Polymer	Yields ^d	M _n (kDa)	I _p (M _w /M _n)
Example 7 (PCV ^a)	10		
Examples 8,9 (PCVP ^b)	76	10.2	2.1
Example 8, 9 (PCVP ^c)	61	10.5	4.6
Example 10 (PCCVP)	68	7.9	4.4
Example 11 (PCVDPATA)	51	10.2	3.7
Example 12 (PCVDPAP)	66	28.2	4.3
Example 13 (PCVBN)	24	4.1	1.2
Example 14 (PPCVT ^a)	10		

^a PCV and PPCVT are insoluble in THF

^b Synthesized by Wittig reaction

^c Synthesized by Wittig-Homer reaction

^d Calculated from the soluble part of the polymer

Figure 5

Polymer	Solution λ_{max}		Thin film λ_{max}		Φ_F
	Abs.	Emi.	Abs.	Emi. ^a	
PCV (Example 7)	426	469 (499)	430		0.52
PCVP (Examples 7,8)	456	505 (539)	456		0.40
PCCVP (Example 10)	481	546 (586)	502	658	0.67
PCVDPATA (Example 11)	440	526	440		0.27
PCVDPAP (Example 12)	472	547 (655)	500	655	0.26
PCVBN (Example 13)	396	440 (467)	398		0.56
PPCVT (Example 14)					

^a Solid state fluorescence can only be observed for PCCVP and PCVDPAP

Figure 6

Oligomer	λ_{max} sol.	$E_{\text{peak ox}}$ ($E_{\text{onset ox}}$) V vs. SCE	E_{g} optical (eV)
PCP (Example 1)	376	1.26 (1.09)	2.92
CCC (Example 2)	402	1.03 (0.91)	2.73
CTTC (Example 3)	453	0.92 (0.81)	2.36
BPCBP (Example 4)	392	1.24 (1.03)	2.78
PCP-CN (Example 5)	399	1.58 (1.41)	2.63
H-CPC-H (Example 6)	399	0.99 (0.76)	2.78

Figure 7




Figure 8

A. CLASSIFICATION OF SUBJECT MATTER
IPC⁶ C07D 209/86, C08F 26/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC⁶ C07D 209/86, C08F 26/12

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base, and, where practicable, search terms used)

Canadian Patent Database, Delphion, STN

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 03/022816 A1 (EQUISTAR CHEMICALS, LP) 20 March 2003, page 2, lines 11-28.	1
X	US 5902884 (CLARIANT GMBH) 11 May 1999, column 2, lines 16-52 and examples 1 to 8.	1
X	CA 2196046 (SANKYO COMPANY) 08 February 1996, pages 5 to 9.	1
X	CA 1026348 (HOFFMAN-LA ROCHE LIMITED) 14 February 1978, page 2.	1
X	Limburg, W.W.; Yanus, J.F.; Williams, D.J.; Goedde, A.O.; Pearson, J.M. Anionic Polymerization of N-Ethyl-2-Vinylcarbazole and N-Ethyl-3-Vinylcarbazole. <i>Journal of Polymer Science, Polymer Chemistry Edition</i> , 1975, 13(5), 1133-9, whole document.	1, 2, 28, 44 and 100
X	Ambrose, J.F.; Nelson, R.F. Anodic Oxidation Pathways of Carbazoles. <i>J. Electrochem. Soc.</i> , 1968, 115, 1159-1164, whole document.	1
X	Registry Number 86-74-8 CAPLUS (9H-Carbazole)	1
X	Registry Number 1484-12-4 CAPLUS (9-Methyl-Carbazole)	1
X	Registry Number 86-28-2 CAPLUS (9-Ethyl-Carbazole)	1
X	Registry Number 1484-08-8 CAPLUS (9-Butyl-Carbazole)	1
X	Registry Number 1150-62-5 CAPLUS (9-Phenyl-Carbazole)	1

Further documents are listed in the continuation of Box C. ☒ X

Patent family members are listed in annex. ☒ X

* Special categories of cited documents :	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier application or patent but published on or after the international filing date	"Y" document considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international-type search
10 November 2004 (10.11.2004)

Date of mailing of the international-type search report
24 December 2004 (24-12-2004)

Name and mailing address of the ISA/
Commissioner of Patents
Canadian Patent Office - PCT
Ottawa/Gatineau KIA 0C9
Facsimile No. 1-819-953-9358

Authorized officer
Edith Lacasse (819) 934-2325

C (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	Registry number 56166-62-2 CAPLUS (9-ethyl-Carbazole-2-carboxaldehyde)	1, 2 and 28
X	Registry number 3110-89-1 CAPLUS (9-methyl-Carbazole-2,7-dicarboxaldehyde)	1 to 4
Y	CA 2360826 (UNIVERSITÉ LAVAL) 30 April 2002, page 2, lines 15-24.	1 to 139
Y	Liu, B.; Yu, W.-L.; Pei, J.; Liu, S.-Y.; Lai, Y.-H.; Huang, W. Design and Synthesis of Bipyridyl-Containing Conjugated Polymers: Effects of Polymer Rigidity on Metal Ion Sensing. <i>Macromolecules</i> , 2001, 34(23), 7932-7940, whole document.	1 to 139
Y	Goldoni, F.; Janssen, A.J.; Meijer, E.W. Synthesis and Characterization of New Copolymers of Thiophene and Vinylene: Poly(thienylenevinylene)s and Poly(terthienylenevinylene)s with Thioether Side Chains. <i>J. Polym. Sci. Part A</i> , 1999, 37, 4629-4639, whole document.	1 to 139
E	WO 2004/070772 A2 (COVION ORGANIC SEMICONDUCTORS GMBH) 19 August 2004, whole document.	1, 44, 45 and 100

Box No. II **Observations where certain claims were found unsearchable (Continuation of Item 2 of first sheet)**

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons :

1. ☐ Claims Nos. :
because they relate to subject matter not required to be searched by this Authority; namely:

2. ☒ Claims Nos.: 44 (in part) and 100 (in part)

because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically :

due to the lack of support and the broadness of claims 44 and 100, the search of claims 44 and 100 was limited to polymerization products of 2-functionalized and 2,7-difunctionalized carbazole derivatives and to the examples given in figures 1 to 4.

3. ☐ Claims Nos. :
because they are dependant claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box III **Observation where unity of invention is lacking (Continuation of item 3 of first sheet)**

This International Searching Authority found multiple inventions in this international application, as follows :

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.

2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos. :

4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos. :

Remark on Protest ☐ The additional search fees were accompanied by the applicant's protest.
 ☐ No protest accompanied the payment of additional search fees.

Patent Document Cited in Search Report	Publication Date	Patent Family Member(s)	Publication Date
WO03022816	20-03-2003	US6455704 B1 WO03022816 A1	24-09-2002 20-03-2003
US5902884	11-05-1999	DE19705466 A1 DE59802385D D1 EP0858995 A1 JP10279558 A US5902884 A	20-08-1998 24-01-2002 19-08-1998 20-10-1998 11-05-1999
CA2196046	08-02-1996	AU666426 B2 AU3088695 A CA2196046 A1 CN1166169 A CZ9700241 A3 EP0804416 A1 FI970323 A GB9415175D D0 GB9423948D D0 HU76923 A2 JP10503488T T NO970308 A NZ290199 A RU2152385 C1 US5877199 A WO9603377 A1	05-02-1998 22-02-1996 08-02-1996 26-11-1997 13-08-1997 05-11-1997 27-03-1997 14-09-1994 11-01-1995 28-01-1998 31-03-1998 25-03-1997 29-06-1999 10-07-2000 02-03-1999 08-02-1996
CA1026348	14-02-1978	AR205331 A1 AT325607B B AT349773 A AU475534 B2 AU5689073 A BE802596 A1 CA1026348 A1 CH587819 A5 DD107681 A5 DE2337340 A1 DK138537B B ES417167 A1 ES442684 A1 ES442685 A1 FI592448 B FR2193611 A1 GB1385620 A HK49876 A HU167611 B IE37942 B1	30-04-1976 27-10-1975 15-01-1975 26-08-1976 23-01-1975 21-01-1974 14-02-1978 13-05-1977 12-08-1974 14-02-1974 25-09-1978 01-05-1976 16-05-1977 16-05-1977 31-03-1981 22-02-1974 26-02-1975 08-09-1976 28-11-1975 23-11-1977
CA2360626	30-04-2002	CA2324757 A1 CA2360626 A1 US2002103332 A1	30-04-2002 30-04-2002 01-08-2002
WO 2004/070772 A2	19-08-2004	DE10304819 A1	19-08-2004